



# CEWELD 316LSi Tig

**TYPE** Stainless steel Tig welding wire (rod) for GTAW welding CrNiMo 316 steels. ( Type 1.4430, 19 12 3 LSi)

**APPLICATIONS** The alloy is widely used in the chemical and food-processing industries, as well as in shipbuilding and various types of architectural structure.

**PROPERTIES** CEWELD® 316LSi Tig offers good general corrosion resistance, particularly to corrosion in acid and chlorinated environments. The alloy has a low carbon content which makes it particularly recommended when there is a risk of intergranular corrosion. The higher silicon content improves the welding properties such as wetting and results in a bright seam.

**CLASSIFICATION**

|        |                        |
|--------|------------------------|
| AWS    | A 5.9: ER316LSi        |
| EN ISO | 14343-A: W 19 12 3 LSi |
| F-nr   | 6                      |
| FM     | 5                      |
| W.Nr.  | 1.4430                 |

**SUITABLE FOR** **ISO 15608: 8.1 Austenit  $\leq$  19 % Cr , TÜV 1000: Gr. 21-30,**  
1.4583, 1.4435, 1.4436, 1.4404, 1.4406, 1.4408, 1.4401, 1.4571, 1.4580, 1.4406, 1.4521, 1.4301, 1.4306,  
X102CrNiMoNb 18 12, X2CrNiMo 18 14 3 (TP), X4CrNiMo 17 13 3, X2CrNiMo 17 12 2 (TP), X 5CrNiMo 19 11 2, X4CrNiMo 17 12 2 (TP), X6CrNiMo 17 12 2, X6CrNiMoNb 17 12 3, X2CrNiMoN 17 12 3 (TP), X2CrMoTi18-2  
316Cb, 316L, 316L, 316LN, 316H, 316, 316Ti, 316Cb, 316LN, 444  
S31640, S31603, S31653, S31600, S31630, S44400

**APPROVALS** TÜV (TÜV (12388.00)) CE DB ((43.206.04))

**WELDING POSITIONS**



**TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)**

| C    | Si  | Mn  | P    | S    | Cr | Ni | Mo  |
|------|-----|-----|------|------|----|----|-----|
| 0.02 | 0.8 | 1.8 | 0.01 | 0.01 | 19 | 12 | 2.8 |

**ALL WELD MECHANICAL PROPERTIES**

| Heat Treatment | R <sub>P0,2</sub><br>MPa | R <sub>m</sub><br>MPa | A <sub>5</sub><br>(%) | Impact Energy (J) ISO-V<br>RT | Impact Energy (J) ISO-V<br>-196°C |
|----------------|--------------------------|-----------------------|-----------------------|-------------------------------|-----------------------------------|
| As Welded /    | 440                      | 620                   | 37                    | 120                           | 55                                |

**REDRYING TEMPERATURE** Not required

**GAS ACCORDING EN 14175** I1



# CEWELD 316LSi Tig

|                         |      |         |               |
|-------------------------|------|---------|---------------|
| 316LSi TIG 0,8 X 1000MM | Type | KG/unit | EANCode       |
|                         | Tube | 5       | 8720663414854 |
| 316LSi TIG 1,0 X 1000MM | Type | KG/unit | EANCode       |
|                         | Tube | 5       | 8720663414892 |
|                         | Tube | 5       | 8720663414861 |
| 316LSi TIG 1,2 X 1000MM | Type | KG/unit | EANCode       |
|                         | Tube | 5       | 8720663414939 |
|                         | Tube | 5       | 8720663414908 |
| 316LSi TIG 1,6 X 1000MM | Type | KG/unit | EANCode       |
|                         | Tube | 5       | 8720663414946 |
| 316LSi TIG 1,6 X 500MM  | Type | KG/unit | EANCode       |
|                         | Tube | 5       | 8720663414960 |
| 316LSi TIG 2,0 X 1000MM | Type | KG/unit | EANCode       |
|                         | Tube | 5       | 8720663414991 |
| 316LSi TIG 2,4 X 1000MM | Type | KG/unit | EANCode       |
|                         | Tube | 5       | 8720663415035 |
| 316LSi TIG 3,2 X 1000MM | Type | KG/unit | EANCode       |
|                         | Tube | 5       | 8720663415073 |
| 316LSi TIG 4,0 X 1000MM | Type | KG/unit | EANCode       |
|                         | Tube | 5       | 8720663415097 |