



CEWELD Alloy C-2000

TYPE NiCrMo based Mig welding wire for Hastelloy C2000

APPLICATIONS CEWELD® Alloy C-2000 (UNS N06200) is unique among the versatile nickel-chromium-molybdenum materials in having a deliberate copper addition

PROPERTIES Like other nickel alloys, it is ductile, easy to form and weld, and possesses exceptional resistance to stress corrosion cracking in chloride-bearing solutions (a form of degradation to which the austenitic stainless steels are prone). It is able to withstand a wide range of oxidizing and non-oxidizing chemicals, and exhibits outstanding resistance to pitting and crevice attack in the presence of chlorides and other halides.

CLASSIFICATION

AWS	A 5.14: ERNiCrMo-17
EN ISO	18274: S Ni 6200(NiCr23Mo16Cu2)
F-nr	43
FM	6
W.Nr.	2.4675

SUITABLE FOR Alloy C-2000, 2.4675, Ni99,2, Nickel 200

APPROVALS No Approvals Found

WELDING POSITIONS



TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)

C	Si	Mn	Cr	Ni	Mo	Fe	Co	Cu
0.01	0.08	0.4	23	60	16	1.5	1	1.6

ALL WELD MECHANICAL PROPERTIES

Heat Treatment	R _{P0,2} MPa	R _m MPa	A ₅ (%)	Impact Energy (J) ISO-V RT
As Welded /	550	830	45	195

REDRYING TEMPERATURE Not required

GAS ACCORDING EN 14175 I1



CEWELD Alloy C-2000

ALLOY C-2000 1,2MM

Type	KG/unit	EANCode
BS-300		8720663419941