



# CEWELD AA DUR 6

**TYPE** Cobalt based (Stellite 6) fluxcored welding wire (FCAW) for overlay welding.

**APPLICATIONS** Cladding valves, Steam-valves, high temperature liquid pumps, hot cutting tools, exhaust valves, seats, cutting knives, metal to metal wear, bearing surfaces, chemical industry, hot shear blades etc. Cladding valves, Steam-valves, high temperature liquid pumps, hot cutting tools, exhaust valves, seats, cutting knives, metal to metal wear, bearing surfaces, chemical industry, hot shear blades etc.

**PROPERTIES** Outstanding alloy against abrasion, thermo-shock and corrosion combined with high temperatures. The weld deposit can be machined with tungsten tool tips and by grinding. The hardness of the weld deposit will decrease 16% at 300°C and about 30% at 600°C. Excellent alloy against thermal shock, abrasion, erosion, corrosion and cavitation at high temperature.

**CLASSIFICATION**

AWS	A 5.21: ERCCoCr-A
EN ISO	14700: T Co2
DIN	8555: MSG 20-GF-40-CTZ
F-nr	71

**SUITABLE FOR** ER CoCr-A  
Stellite 6

**APPROVALS** No Approvals Found

**WELDING POSITIONS**



**TYPICAL CHEMICAL ANALYSIS OF WELD METAL (%)**

C	Si	Mn	Cr	Ni	Mo	Fe	W	Co
1	1	0.8	28	2	0.01	3	4.5	Rem.

**ALL WELD MECHANICAL PROPERTIES**

Heat Treatment	R <sub>p0,2</sub> MPa	R <sub>m</sub> MPa	A <sub>5</sub> (%)	Hardness Rockwell C
As Welded /				Avg. 43

**REDRYING TEMPERATURE** 140°C / 24 hr

**GAS ACCORDING EN 14175** M13



# CEWELD AA DUR 6

AA DUR 6 0,8MM

Type	KG/unit	EANCode
BS-300	15	8720663402011

AA DUR 6 1,2MM

Type	KG/unit	EANCode
BS-300	15	8720663402028

AA DUR 6 1,6MM

Type	KG/unit	EANCode
BS-300	15	8720663402042