



CEWELD SACW DUR 21

TYPE Cobalt based fluxcored SAW wire for cladding against metal to metal wear, thermal shock and erosion.


APPLICATIONS Solving wear problems against chemicals, erosion, corrosion, high temperatures, abrasion and combinations of those.

PROPERTIES Excellent gliding properties against metal to metal wear due to low friction, Excellent against erosion and corrosion at high working temperatures upto 900°C. Crack free hard facing deposit against severe thermal shock and impact. To be used with fused flux CEWELD® FL 880.

CLASSIFICATION EN ISO 14700: T Co1

SUITABLE FOR Cladding seats and valves in chemical industry, hot sharing blades, extrusion parts, coke hammers, turbine injectors, gas and steam turbine parts.

APPROVALS No Approvals Found

WELDING POSITIONS 

TYPICAL CHEMICAL ANALYSIS OF WELD METAL (%)	C	Si	Mn	Cr	Ni	Mo	Fe	Co
	0.27	1.2	1	28	2.5	5	3.5	Rem.

ALL WELD MECHANICAL PROPERTIES	Heat Treatment	RP0,2 MPa	Rm MPa	A5 (%)	Hardness Rockwell C
	As Welded /				Avg. 30

REDRYING TEMPERATURE 140°C / 24 hr

GAS ACCORDING EN 14175



CEWELD SACW DUR 21

SACW DUR 21 2,4MM

Type	KG/unit	EANCode
K-415	25	8720663417336