



CEWELD OA 58-66B

TYPE High alloyed seamless flux cored wire for hardfacing against extreme abrasion.

APPLICATIONS Rebuilding wornout parts or protecting new machine parts to increase life that suffer from extreme

abrasive wear

PROPERTIES High C-, Cr-, B-alloyed flux-cored wire electrode which forms extremely hard carbides for extremely

hard deposits on parts subject to excessively heavy abrasive wear weldable with and without protective gas. Verry good wear resistance due to excellent first layer hardness properties. More than 1 or 2 layers should not be deposited. A Buffer layer with CEWELD® OA 4370 or CEWELD® OA MnCr is recommended in case of old layers or critical base metals. Weldable with M21 or without

shielding gas.

CLASSIFICATION EN ISO 14700: T ZFe14

SUITABLE FOR 58-66 HRc Hardfacing alloy used in mining, agriculture and steel mills, conveyor chains, agriculture,

construction, mixer blades, paddles, cement pumps with excelent abrasion and wear resistance

against sand and minerals

APPROVALS No Approvals Found

WELDING POSITIONS

PA PB PC PC

TYPICAL CHEMICAL ANALYSIS OF WELD METAL

(%)

ALL WELD MECHANICAL PROPERTIES

| Heat | R _{P0,2} | Rm | A5 | Hardness | |
|-----------|-------------------|-----|-----|------------|--|
| Treatment | MPa | MPa | (%) | Rockwell C | |

Avg. 62

REDRYING TEMPERATURE

140°C / 24 hr

As Welded /

GAS ACCORDING EN 14175