







CEWELD AA B CrMo1V

TYPE	High basic flux-cored wire for M21 shielding gas. (Typ CrMo1V, 1.7745)																		
APPLICATIONS	Foundries, production welding																		
PROPERTIES	CEWELD® AA BCrMo1V is a basic cored wire with Excellent weld puddle manipulation. Low spatter loss, easy slag removal. Extremely crack resistant. Suitable for economic welding of CrMoV-steels up to 550 °C. Due to the seamless production process the hydrogen content is below 3ml/100g weld metal even after long storage in unconditioned condition.																		
CLASSIFICATION	<table border="0"> <tr> <td>AWS</td> <td>A 5.29: E80T5-B2M H4</td> </tr> <tr> <td>AWS</td> <td>A 5.36: E80T5-M21P4-B2-H4</td> </tr> <tr> <td>EN ISO</td> <td>17634-A: T Z B M 4 H5</td> </tr> <tr> <td>F-nr</td> <td>6</td> </tr> <tr> <td>FM</td> <td>4</td> </tr> <tr> <td>W.Nr.</td> <td>~1.7745</td> </tr> </table>	AWS	A 5.29: E80T5-B2M H4	AWS	A 5.36: E80T5-M21P4-B2-H4	EN ISO	17634-A: T Z B M 4 H5	F-nr	6	FM	4	W.Nr.	~1.7745						
AWS	A 5.29: E80T5-B2M H4																		
AWS	A 5.36: E80T5-M21P4-B2-H4																		
EN ISO	17634-A: T Z B M 4 H5																		
F-nr	6																		
FM	4																		
W.Nr.	~1.7745																		
SUITABLE FOR	<p>Type 1Cr0,5Mo,V ISO 15608: ~5,1 1.7335, 1.7262, 1.7728, 1.7218, 1.7225, 1.7258, 1.7354, 1.7357, 1.7745, 1.7706, 1.7733 13CrMo4-5, 15CrMo5, 15 CrMoV 5 10, 16CrMoV4, 25CrMo4, 42CrMo4, 24CrMo5, G22CrMo5-4, G17CrMo5-5, 24CrMoV5-5, G17CrMoV5-10 ASTM A 182 Gr. F12; A 193 Gr. B7; A 213 Gr. T12; A 217 Gr. WC6; A 234 Gr. WP11; A335 Gr. P11, P12; A 336 Gr. F11, F12; A 426 Gr. CP12</p>																		
APPROVALS	No Approvals Found																		
WELDING POSITIONS	<div style="display: flex; gap: 10px;">    </div>																		
TYPICAL CHEMICAL ANALYSIS OF WELD METAL (%)	<table border="1" style="width: 100%; border-collapse: collapse; text-align: center;"> <thead> <tr> <th>C</th> <th>Si</th> <th>Mn</th> <th>P</th> <th>S</th> <th>Cr</th> <th>Ni</th> <th>Mo</th> <th>V</th> </tr> </thead> <tbody> <tr> <td>0.1</td> <td>0.3</td> <td>0.9</td> <td>0.15</td> <td>0.015</td> <td>1.2</td> <td>0.3</td> <td>1.1</td> <td>0.25</td> </tr> </tbody> </table>	C	Si	Mn	P	S	Cr	Ni	Mo	V	0.1	0.3	0.9	0.15	0.015	1.2	0.3	1.1	0.25
C	Si	Mn	P	S	Cr	Ni	Mo	V											
0.1	0.3	0.9	0.15	0.015	1.2	0.3	1.1	0.25											
ALL WELD MECHANICAL PROPERTIES	<table border="1" style="width: 100%; border-collapse: collapse; text-align: center;"> <thead> <tr> <th rowspan="2">Heat Treatment</th> <th rowspan="2">R_{P0,2} MPa</th> <th rowspan="2">R_m MPa</th> <th rowspan="2">A₅ (%)</th> <th colspan="2">Impact Energy (J) ISO-V</th> </tr> <tr> <th colspan="2">RT</th> </tr> </thead> <tbody> <tr> <td>690°C±15°C /3h</td> <td>500</td> <td>620</td> <td>20</td> <td colspan="2">70</td> </tr> </tbody> </table>	Heat Treatment	R _{P0,2} MPa	R _m MPa	A ₅ (%)	Impact Energy (J) ISO-V		RT		690°C±15°C /3h	500	620	20	70					
Heat Treatment	R _{P0,2} MPa					R _m MPa	A ₅ (%)	Impact Energy (J) ISO-V											
		RT																	
690°C±15°C /3h	500	620	20	70															
REDRYING TEMPERATURE	Not required																		
GAS ACCORDING EN 14175	M21																		



CEWELD AA B CrMo1V

AA B CRM01V 1,2MM

Type	KG/unit	EANCode
BS-300	16	8720663423191