



CEWELD AA M Corten

TYPE	Seamless cored wire without slag for M21																
APPLICATIONS	Bridge-, general steel construction. Onshore and Offshore. General engineering. Heavy transportation and rail construction, etc.																
PROPERTIES	CEWELD® AA M Corten is a seamless metal cored wire with remarkable stable arc and no spatters. Excellent for use in automated welding applications such as orbital Mag or robotic welding. This wire offers a unique welding deposit with more less than 1% nickel and 0,5% Cu to make it weather resistant. Due to the seamless production process the hydrogen content is below 3ml/100g weld metal even after long storage in unconditioned environment.																
CLASSIFICATION	<table border="0"> <tr> <td>AWS</td> <td>A 5.28: E80C-W2 H4</td> </tr> <tr> <td>AWS</td> <td>A 5.36: E81T15-M21A4-W2-H4</td> </tr> <tr> <td>EN ISO</td> <td>17632-A: T 46 6 Z M M21 1 H5</td> </tr> <tr> <td>F-nr</td> <td>6</td> </tr> <tr> <td>FM</td> <td>1</td> </tr> </table>	AWS	A 5.28: E80C-W2 H4	AWS	A 5.36: E81T15-M21A4-W2-H4	EN ISO	17632-A: T 46 6 Z M M21 1 H5	F-nr	6	FM	1						
AWS	A 5.28: E80C-W2 H4																
AWS	A 5.36: E81T15-M21A4-W2-H4																
EN ISO	17632-A: T 46 6 Z M M21 1 H5																
F-nr	6																
FM	1																
SUITABLE FOR	<p>CuNi, Reh ≤ 460MPa ISO 15608: 1.4 1.8963, 1.8946, 1.8965 S235JRG2Cu, S235J2G4Cu, S235J0Cu, S235JRW, S355J0Cu, S355J2G3Cu, S355J0W, 235J2W-S355J2W, S355K2W, WTSt 37, WTSt 52, ASTM A 588M Grade A,B, C...K, A 618 Gr. II; A 709 Gr. 50 WF3 CORten A, B, C, Patinax 37</p>																
APPROVALS	CE																
WELDING POSITIONS																	
TYPICAL CHEMICAL ANALYSIS OF WELD METAL (%)	<table border="1"> <thead> <tr> <th>C</th> <th>Si</th> <th>Mn</th> <th>P</th> <th>S</th> <th>Cr</th> <th>Ni</th> <th>Cu</th> </tr> </thead> <tbody> <tr> <td>0.05</td> <td>0.7</td> <td>1.2</td> <td>0.015</td> <td>0.015</td> <td>0.5</td> <td>0.7</td> <td>0.5</td> </tr> </tbody> </table>	C	Si	Mn	P	S	Cr	Ni	Cu	0.05	0.7	1.2	0.015	0.015	0.5	0.7	0.5
C	Si	Mn	P	S	Cr	Ni	Cu										
0.05	0.7	1.2	0.015	0.015	0.5	0.7	0.5										
ALL WELD MECHANICAL PROPERTIES	<table border="1"> <thead> <tr> <th rowspan="2">Heat Treatment</th> <th rowspan="2">R_{p0,2} MPa</th> <th rowspan="2">R_m MPa</th> <th rowspan="2">A₅ (%)</th> <th colspan="2">Impact Energy (J) ISO-V</th> </tr> <tr> <th>-20°C</th> <th>-40°C</th> </tr> </thead> <tbody> <tr> <td>As Welded /</td> <td>510</td> <td>650</td> <td>22</td> <td>100</td> <td>70</td> </tr> </tbody> </table>	Heat Treatment	R _{p0,2} MPa	R _m MPa	A ₅ (%)	Impact Energy (J) ISO-V		-20°C	-40°C	As Welded /	510	650	22	100	70		
Heat Treatment	R _{p0,2} MPa					R _m MPa	A ₅ (%)	Impact Energy (J) ISO-V									
		-20°C	-40°C														
As Welded /	510	650	22	100	70												
REDRYING TEMPERATURE	Not required																
GAS ACCORDING EN 14175	M21																



CEWELD AA M Corten

AA M CORTEN 1,2MM

Type	KG/unit	EANCode
K-300	16	8720663405395