




CEWELD 4501 Kb

TYPE	Basic core wire alloyed electrode for welding Super Duplex																		
APPLICATIONS	Welding wrought, forged or cast super duplex stainless steels for service in the as-welded condition. Heterogeneous welding between super duplex stainless steels and dissimilar welds between other stainless and mild or low alloyed steels.																		
PROPERTIES	CEWELD® 4501 Kb is a basic coated electrode with a fully alloyed core, the duplex weld deposit provides excellent resistance to pitting, chloride stress corrosion cracking and intercrystalline corrosion due to the high CrMo(N) content (Pitting index >40). Furthermore, the weld metal alloy is saltwater-proof and offers high tensile strength, as a result of nitrogen being added to the alloy.																		
CLASSIFICATION	<table border="0"> <tr> <td>AWS</td> <td>A 5.4: E 2595-15</td> </tr> <tr> <td>EN ISO</td> <td>3581-A: E 25 9 4 N L</td> </tr> <tr> <td>F-nr</td> <td>5</td> </tr> <tr> <td>FM</td> <td>5</td> </tr> <tr> <td>W.Nr.</td> <td>1.4501</td> </tr> </table>	AWS	A 5.4: E 2595-15	EN ISO	3581-A: E 25 9 4 N L	F-nr	5	FM	5	W.Nr.	1.4501								
AWS	A 5.4: E 2595-15																		
EN ISO	3581-A: E 25 9 4 N L																		
F-nr	5																		
FM	5																		
W.Nr.	1.4501																		
SUITABLE FOR	UNS S32550 :UR 52 N, Ferralium 255, UNS S32520 :UR 52 N+, UNS S32750 :SAF 2507, UR 47 N+, UNS S32760 :ZERON 100, UNS 32760, UR 76 N, SM22Cr, SAF 2507, ASTM S32760 (ZERON 100), S32550 and S31260., It can also be used for welding duplex type 2205, 1.4460, 1.4462, 1.4463, 1.4515, 1.4517, 1.4507 URANUS 52N, SAF 25.07, GX 3 CrNiMoCuN 26-6-3, (1.4515), GX 3 CrNiMoCuN 26-6-3-3, (1.4517), 25% Cr Super Duplex steels SAF 25/07, S32750 1.4410 - 25Cr-7Ni-4Mo-0.28N SAF2507, NAS74N, S32760 1.4501 - 25Cr-7Ni-3.8Mo-0.7Cu-0.7W-0.25N, S32506 - SUS329J4L 25Cr-7Ni-3Mo-0.15N-0.2W NAS64 1.4507, S31803, S32205,																		
APPROVALS	No Approvals Found																		
WELDING POSITIONS																			
TYPICAL CHEMICAL ANALYSIS OF WELD METAL (%)	<table border="1"> <thead> <tr> <th>C</th> <th>Si</th> <th>Mn</th> <th>Cr</th> <th>Ni</th> <th>Mo</th> <th>N</th> <th>W</th> <th>Cu</th> </tr> </thead> <tbody> <tr> <td>0.036</td> <td>0.84</td> <td>0.83</td> <td>26.15</td> <td>9.46</td> <td>3.73</td> <td>0.21</td> <td>0.67</td> <td>0.63</td> </tr> </tbody> </table>	C	Si	Mn	Cr	Ni	Mo	N	W	Cu	0.036	0.84	0.83	26.15	9.46	3.73	0.21	0.67	0.63
C	Si	Mn	Cr	Ni	Mo	N	W	Cu											
0.036	0.84	0.83	26.15	9.46	3.73	0.21	0.67	0.63											
ALL WELD MECHANICAL PROPERTIES	<table border="1"> <thead> <tr> <th>Heat Treatment</th> <th>R_{p0,2} MPa</th> <th>R_m MPa</th> <th>A₅ (%)</th> <th>Impact Energy (J) ISO-V RT</th> </tr> </thead> <tbody> <tr> <td>As Welded /</td> <td>560</td> <td>730</td> <td>23</td> <td>50</td> </tr> </tbody> </table>	Heat Treatment	R _{p0,2} MPa	R _m MPa	A ₅ (%)	Impact Energy (J) ISO-V RT	As Welded /	560	730	23	50								
Heat Treatment	R _{p0,2} MPa	R _m MPa	A ₅ (%)	Impact Energy (J) ISO-V RT															
As Welded /	560	730	23	50															
REDRYING TEMPERATURE	300°C / 2 hr																		
GAS ACCORDING EN 14175																			



CEWELD 4501 Kb

4501 KB 2,5 X 300MM

Type	KG/unit	EANCode
Can	2,5	8720663424341