

CEWELD E DUR 49

TYPE	Fe, Cr, Co and Mo based elektrode. (Fe3,
APPLICATIONS	The most common areas of application from CEWELD E DUR 49 are: Hardfacing of forging presses, hot piercing dies, stretching rolls, pinch rolls, hot strip mill table rolls and back-up
PROPERTIES	CEWELD E DUR 49 has a stainless weld metal based on Fe, Cr, Co, Mo. This alloy has a high hot and hot wear resistance, high resistance to sliding wear of metallic sliding wear of metallic objects. It has good hardness retention up to 650° C and is scale resistant up to up to 900° C as well as thermal shock resistant and resistant to sudden temperature fluctuations. Work hardening. Not crack sensitive. The number of layers can be applied as required.
CLASSIFICATION	EN ISO 14700: E Fe3

SUITABLE FOR	1.2311 40CrMnMo 7 1.2343 X38CrMoV 5 1 1.2344 X40CrMoV 5 1 1.2365 X32CrMoV 3 3 1.2367 X38CrMoV 5 3 1.2606 X37CrMoW 5 1 1.2713 55NiCrMoV 6 1.2714 56NiCrMoV 7
--------------	--

APPROVALS No Approvals Found


WELDING POSITIONS	
-------------------	---

TYPICAL CHEMICAL ANALYSIS OF WELD METAL (%)	C	Si	Mn	Cr	Mo	Fe	Co
	0.15	0.6	0.6	14	2.3	Rem.	13

ALL WELD MECHANICAL PROPERTIES	Heat Treatment	R _{P0,2} MPa	R _m MPa	A ₅ (%)	Hardness Rockwell C
	As Welded /				Avg. 48

REDRYING TEMPERATURE 300°C / 2 hr

GAS ACCORDING EN 14175



CEWELD E DUR 49

E DUR 49 3,2 X 350MM

Type	KG/unit	EANCode
Can	3	8720663402141