



CEWELD NiFe 55 Tig

TYPE Nickel iron welding rod for joining multiple pass welding cast iron. (NiFe-2, 2.4472)

APPLICATIONS CEWELD® NiFe 55 Tig is suitable for welding mild and low alloy steels which are exposed to

termperatures up to 450C. Multiple pass welding of spheroidal graphite cast irons and neutral tempered (black) malleable cast irons. Cast Iron repairs, rebuilding shafts, wheels, critical joints

between steel and cast iron etc

PROPERTIES CEWELD® NiFe 55 Tig is a nickel Iron based filler metal for joint welding and claddings on cast Iron.

Very wel suited also for dissimilar welding between cast iron and high alloyed stainless and heat resistant steels or mild steels. Excellent Weldabillity with extreme crack resistance with a ductile weld deposit. Good welding and wetting characteristics and high resistance against porosity. The weld metal is corrosion and heat resistant. Very well suitable for welding with robotics or

automated processes.

CLASSIFICATION AWS A 5.15: E NiFe-CI

EN ISO 1071: S C NiFe-2

W.Nr. 2.4472

Si

0.13

SUITABLE FOR Grey cast iron, malleable, nodular : NF A 32-101 : FGL 150, 200, 250, 300, 350, 400. NF A 32-201 :

FGS 370-17, 400-12, 500-7, 600-3, 700-2. NF A 32-702: MN 350-10, 380-18, 450-6, 350-4, 650-3. DIN 1691: CG-14, 18, 25, 30. DIN 1693: GGG-40, 50, 60, 70. DIN 1692: GTS-35, 45, 55, 65, 70.

S

0.001

55

Fe

Rem.

Сп

0.03

APPROVALS No Approvals Found

WELDING POSITIONS

PA PB PC PD PE PF PG

Mn

0.7

TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)

ALL WELD MECHANICAL

PROPERTIES

Heat Treatment	R _{P0,2}	Rm	A5
Treatment	MPa	MPa	(%)

0.005

REDRYING TEMPERATURE

Not required

As Welded /

C

0.01

GAS ACCORDING EN 14175





CEWELD NiFe 55 Tig

NIFE 55 TIG 1,6 X 1000MM	Туре	KG/unit	EANCode
	Tube	5	8720663424181
NIFE 55 TIG 2,0 X 1000MM	Type	KG/unit	EANCode
	Tube	5	8720663420756
	Tube	5	8720663417817
NIFE 55 TIG 2,4 X 1000MM	Туре	KG/unit	EANCode
	Tube	5	8720663420763