



CEWELD CuSn12 Tig

TYPE Tin bronze alloy with high percentage of tin for virtually all welding procedures

APPLICATIONS Boilers and tubes out of copper or copper alloys, oven soldering etc.

PROPERTIES Very good deoxidization and high hardness similar to cast bronzes. Surfacing and joining of Copper and CuSn-Alloys. Widely used and recommended for oven soldering. High quality alloyed copper wire. Sound, pore free deposits and good electrical conductivity. Excellent corrosion resistance

CLASSIFICATION EN ISO 24373: Cu 5410 / CuSn12P
W.Nr. 2.1056

SUITABLE FOR Tin bronze alloy with high percentage of tin for virtually all welding procedures. Very good deoxidisation and high hardness similar to cast bronzes. Surfacing and joining of Copper and CuSn-alloys. Widely used and recommended for oven soldering.
Mat.n: 2.1016, 2.1020, 2.1030, 2.1050, 2.1052, 2.1056, 2.1080, 2.1086, 2.1090
CuSn8, CuSn7, CuSn6, CuSn4, G-CuSn7ZnPb, G-CuSn10

APPROVALS No Approvals Found

WELDING POSITIONS



TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)

P	Cu	Zn	Pb	Sn
0.25	Rem.	0.03	0.01	12

ALL WELD MECHANICAL PROPERTIES

Heat Treatment	R _{P0,2} MPa	R _m MPa	A ₅ (%)	Hardness Brinell
As Welded /		350		Avg. 120

REDRYING TEMPERATURE Not required

GAS ACCORDING EN 14175 I1



CEWELD CuSn12 Tig

CUSN12 TIG 1,6 X 1000MM	Type	KG/unit	EANCode
	Tube	5	8720663422835
CUSN12 TIG 2,0 X 1000MM	Type	KG/unit	EANCode
	Tube	5	8720663422842
CUSN12 TIG 3,0 X 1000MM	Type	KG/unit	EANCode
	Tube	5	8720663422859
CUSN12 TIG 4,0 X 1000MM	Type	KG/unit	EANCode
	Tube	5	8720663422866