









CEWELD NiCrBSi 4 Tig (Colmonoy 4)

TYPE	Nickel based Tig filler metal for hardfacing and overlay applications.					
APPLICATIONS	NiCrBSi 4 TIG offers outstanding metallurgical and physical properties making them ideally suited to solving wear mechanisms such as abrasion, erosion, corrosion and high-temperatures encountered in service.					
PROPERTIES	This nickel based alloy offers superior wear protection, retaining its hardness up to 600°C (1000°F) with significant resistance to oxidation.					
CLASSIFICATION	AWS		A 5.21: ERNiCr-A			
SUITABLE FOR	Aircraft gas turbines, steam turbine powerplants, turbochargers and valves in reciprocating engines, prosthetic devices, heat treating equipment, pollution control equipment, coal gasification and liquefaction systems, and components in pulp and paper mills.					
APPROVALS	No Approvals Found					
WELDING POSITIONS	<div>PAPBPCPDPEPF</div>					
TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)	C	Ni	Cr	B	Si	Fe
	0.4	Rem.	10	2.4	2.1	2.8
ALL WELD MECHANICAL PROPERTIES	Heat Treatment	R _{P0,2} MPa	R _m MPa	A5 (%)	Hardness Rockwell C	
	As Welded /				Avg. 37.5	
REDRYING TEMPERATURE	Not required					
GAS ACCORDING EN 14175	I1					