



CEWELD 316L Tig

TYPE Solid stainless steel filler metal with excellent resistance against general corrosion.(Type 19 12 3L, 1.4430)

APPLICATIONS The alloy is widely used in the chemical and food-processing industries, as well as in shipbuilding and various types of architectural structure.

PROPERTIES Stainless steel with excellent resistance to intercrystalline corrosion and wet corrosion up to 350°C (662 °F). Corrosion-resistance is similar to low-carbon CrNiMo steels/cast steel grades

CLASSIFICATION

AWS	A 5.9: ER316L
EN ISO	14343-A: W 19 12 3 L
F-nr	6
FM	5
W.Nr.	1.4430

SUITABLE FOR **ISO 15608: 8.1 Austenitic ≤ 19 % Cr , TÜV 1000: Gr. 21-30,**
 1.4583, 1.4435, 1.4436, 1.4404, 1.4406, 1.4408, 1.4401, 1.4571, 1.4580, 1.4406, 1.4521
 X102CrNiMoNb 18 12, X2CrNiMo 18 14 3 (TP), X4CrNiMo 17 13 3, X2CrNiMo 17 12 2 (TP), X 5CrNiMo
 19 11 2, X4CrNiMo 17 12 2 (TP), X6CrNiMo 17 12 2, X6CrNiMoNb 17 12 3, X2CrNiMoN 17 12 3 (TP),
 X2CrMoTi18-2
 316Cb, 316L, 316L, 316LN, 316H, 316, 316Ti, 316Cb, 316LN, 444
 S31640, S31603, S31653, S31600, S31630, S44400

APPROVALS No Approvals Found

WELDING POSITIONS



TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)

C	Si	Mn	P	S	Cr	Ni	Mo
0.02	0.5	1.5	0.01	0.01	19	12	2.8

ALL WELD MECHANICAL PROPERTIES

Heat Treatment	R _{P0,2} MPa	R _m MPa	A ₅ (%)	Impact Energy (J) ISO-V	
				RT	-196°C
As Welded /1h	440	610	35	120	45

REDRYING TEMPERATURE Not required

GAS ACCORDING EN 14175 I1



CEWELD 316L Tig

316L TIG 1,0 X 1000MM

Type	KG/unit	EANCode
Tube	5	8720663413642

316L TIG 1,2 X 1000MM

Type	KG/unit	EANCode
Tube	5	8720663413659

316L TIG 1,6 X 1000MM

Type	KG/unit	EANCode
Tube	5	8720663413666

316L TIG 2,0 X 1000MM

Type	KG/unit	EANCode
Tube	5	8720663413673

316L TIG 2,4 X 1000MM

Type	KG/unit	EANCode
Tube	5	8720663413680

316L TIG 3,2 X 1000MM

Type	KG/unit	EANCode
Tube	5	8720663413697