




CEWELD CuAg (LP) Tig

TYPE	Copper based Tig filler metal alloyed with silver				
APPLICATIONS	Electrical contacts, cables, joining copper alloys, rebuilding copper components, installations made from copper tubes etc..				
PROPERTIES	Copper alloy, silver-alloyed-with a slightly higher percentage of phosphor, suitable for MIG welding, easy to handle, high plasticity of the weld metal. • High quality alloyed copper wire • The weld metal is a Copper-Silver alloy • Sound, pore free deposits and high electrical conductivity • Excellent corrosion resistance				
CLASSIFICATION	AWS	A 5.7: ERCu			
	EN ISO	24373: Cu 1897 / CuAg1			
	F-nr	31			
	W.Nr.	2.1211			
SUITABLE FOR	Rebuilding and reconditioning electrical contacts. 2.0040 - OF-Cu, 2.0070 - SE-Cu, 2.0076 - SW-Cu, 2.0090 - SF-Cu				
APPROVALS	No Approvals Found				
WELDING POSITIONS					
TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)	Cu	Cu+Ag			Ag
	99.1	99.9			0.8
ALL WELD MECHANICAL PROPERTIES	Heat Treatment	R _{p0,2} MPa	R _m MPa	A5 (%)	Impact Energy (J) ISO-V
	As Welded /	200		30	RT 75
REDRYING TEMPERATURE	Not required				
GAS ACCORDING EN 14175	11				



CEWELD CuAg (LP) Tig

CUAG (LP) TIG 2,4 X 1000MM

Type	KG/unit	EANCode
Tube	5	8720663408426