



## CEWELD AA NiCro 600

**TYPE** Rutile flux-cored nickel base welding wire for gas shielded arc welding.

**APPLICATIONS** AA NICRO 600 is developed for welding and cladding nickel-based alloys such as alloy 600 or

similar materials. This alloy can also be used for welding dissimilar nickel-based alloys to each other, to alloyed steels or to stainless steels. AA NICRO 600 can also be used on difficult to weld steels! Difficult to weld steel, chain, cock wheels, kiln tyre Dissimilar-welding applications include joining INCONEL alloys, INCOLOY alloys and INCOLOY alloy 330 to nickel, MONEL alloys, stainless

steels, and carbon steels. Joining stainless steels to nickel alloys and carbon steels

**PROPERTIES** High mechanical properties with excellent weldability due to improved wetting compare to solid

wire.

CLASSIFICATION **AWS** A 5.34: E NiCr3T1-4

> EN ISO 12153-A: T Ni 6082 (NiCr20Mn3Nb) R M21 3

F-nr 43 FΜ 6 W.Nr. 2.4806

SUITABLE FOR E NiCr3 / Ni6082 / NiCr20Mn3Nb

1.4816, 1.4864, 1.4876, 1.4583, 1.4886, 1.5637, 1.5662, 1.5680, 1.6900, 1.6901, 1.6903, 1.6906,

2.4630, 2.4631, 2.4669, 2.4816, 2.4817, 2.4851, 2.4867, 2.4870, 2.4951

NiCr20Ti, NiCr21TiAl, NiCr15Fe7TiAl, NiCr15Fe, LC-NiCr15Fe, NiCr23Fe, NiCr60 15, NiCr80 20, NiCr 10, NiCr20Ti 1.5637 12 Ni 14, X8Ni9, 12Ni19, X12CrNI18 9, GX8CrNi18 10, X10CrNiTi18 10,

X5CrNi18 10

UNS Nr: K81340 - N06600 - N06601 - N08800 - N08810

Alloy 600, Alloy 600 L, Alloy 800 / 800H UNS N06600, N07080, N0800, N0810

**APPROVALS** No Approvals Found

WELDING POSITIONS





TYPICAL CHEMICAL

ANALYSIS OF WELD METAL	
(%)	

С	Si	Mn	Cr	Ni	Nb	Ti	Fe
0.045	0.3	5.5	16.5	70	2	0.3	2.1

ALL WELD MECHANICAL **PROPERTIES** 

Heat	R <sub>P0,2</sub>	Rm	A5	Impact Energy (J) ISO-V		
Treatment	MPa	MPa	(%)	0°C	-196°C	
As Welded /	390	650	45	130	125	

REDRYING TEMPERATURE 140°C / 24 hr

**GAS ACCORDING EN 14175** M21





## CEWELD AA NiCro 600

AA NICRO 600 1,2MM Type KG/unit EANCode
BS-300 12,5 8720663418814