







# CEWELD OA 60-70B

TYPE	High alloyed seamless metal cored wire for hardfacing against extreme abrasion.					
APPLICATIONS	Rebuilding wornout parts or protecting new machine parts to increase life that suffer from extreme abrasive wear					
PROPERTIES	High C-, Cr-, B-alloyed flux-cored wire electrode which forms extremely hard carbides for extremely hard deposits on parts subject to excessively heavy abrasive wear weldable with and without protective gas. Extreme good wear resistance due to excelent first layer hardness properties. More than 1 or 2 layers should not be deposited. A Buffer layer with OA 4370 or OA MnCr is recommended in case of old layers or critical base metals..					
CLASSIFICATION	EN ISO	14700: T ZFe13				
	DIN	8555: MF 10-GF-70-G				
SUITABLE FOR	60-70 HRc Hardfacing wire used in mining, agriculture and steel mills, conveyor chains, agriculture, construction, mixer blades, paddles, cement pumps with excelent abrasion and wear resistance against sand and minerals					
APPROVALS	No Approvals Found					
WELDING POSITIONS	<div>   </div>					
TYPICAL CHEMICAL ANALYSIS OF WELD METAL (%)	C	Si	Mn	Cr	Fe	B
	1.8	0.6	0.8	8.2	Rem.	4.2
ALL WELD MECHANICAL PROPERTIES	Heat Treatment	R <sub>P0,2</sub> MPa	R <sub>m</sub> MPa	A <sub>5</sub> (%)	Hardness Rockwell C	
	As Welded /				Avg. 64	
REDRYING TEMPERATURE	Not required					
GAS ACCORDING EN 14175						



# CEWELD OA 60-70B

OA 60-70B 1,6MM

Type	KG/unit	EANCode
BS-300	16	8720663403704