



CEWELD AA B890SR

TYPE	Medium alloyed, high-strength flux-cored wire for M21 shielding gas																			
APPLICATIONS	Crane-, plant-, craft- and steel construction, pipe work, foundries.																			
PROPERTIES	Remarkable crack resistant weld metal in combination with very low hydrogen content. Therefore, suitable for the economic processing of high-strength and low temperature fine-grained structural steels. Excellent welding properties in short and spray arc. Excellent gap bridging for root welds. High deposition rate and no intermediate cleaning required with very low spatter loss. Weld metal is heat treatable.																			
CLASSIFICATION	<table border="0"> <tr> <td>AWS</td> <td>A 5.36: E130T5-M21A4-K4-H4</td> </tr> <tr> <td>EN ISO</td> <td>18276-A: T 89 0 Z B M21 3 H5</td> </tr> <tr> <td>F-nr</td> <td>6</td> </tr> <tr> <td>FM</td> <td>4</td> </tr> </table>	AWS	A 5.36: E130T5-M21A4-K4-H4	EN ISO	18276-A: T 89 0 Z B M21 3 H5	F-nr	6	FM	4											
AWS	A 5.36: E130T5-M21A4-K4-H4																			
EN ISO	18276-A: T 89 0 Z B M21 3 H5																			
F-nr	6																			
FM	4																			
SUITABLE FOR	<p>Reh ≤ 890 MPa ISO 15608: 5.1 1.7220, 1.7225, 1.7228, 1.7336 13 CrMoSi5-5, 13CrMo4-5, 25CrMo4, 26 CrMo4-2, 34CrMo4, 42CrMo4, 50CrMoSi5-5, 28NiCrMo44, (S690Q-S890Q, S690QL-S890QL) ASTM A 829M, A387, SAE 4135-37, 4140-45, 4150 UNS G41350-70, G41400-50, G41500 40CD4, 42CD4 / 40CD4u, 42CD4u Firmodur 7225, 7227., Thyssen TK 7225, 7227</p>																			
APPROVALS	CE																			
WELDING POSITIONS																				
TYPICAL CHEMICAL ANALYSIS OF WELD METAL (%)	<table border="1"> <thead> <tr> <th>C</th> <th>Si</th> <th>Mn</th> <th>P</th> <th>S</th> <th>Cr</th> <th>Ni</th> <th>Mo</th> </tr> </thead> <tbody> <tr> <td>0.05</td> <td>0.5</td> <td>1.5</td> <td>0.015</td> <td>0.015</td> <td>0.5</td> <td>2.2</td> <td>0.5</td> </tr> </tbody> </table>	C	Si	Mn	P	S	Cr	Ni	Mo	0.05	0.5	1.5	0.015	0.015	0.5	2.2	0.5			
C	Si	Mn	P	S	Cr	Ni	Mo													
0.05	0.5	1.5	0.015	0.015	0.5	2.2	0.5													
ALL WELD MECHANICAL PROPERTIES	<table border="1"> <thead> <tr> <th rowspan="2">Heat Treatment</th> <th rowspan="2">R_{p0,2} MPa</th> <th rowspan="2">R_m MPa</th> <th rowspan="2">A₅ (%)</th> <th colspan="2">Impact Energy (J) ISO-V</th> </tr> <tr> <th colspan="2">RT</th> </tr> </thead> <tbody> <tr> <td rowspan="2">As Welded / 620°C±15°C /1h</td> <td>920</td> <td>1010</td> <td>17</td> <td colspan="2">75</td> </tr> <tr> <td>710</td> <td>910</td> <td>18</td> <td colspan="2">55</td> </tr> </tbody> </table>	Heat Treatment	R _{p0,2} MPa	R _m MPa	A ₅ (%)	Impact Energy (J) ISO-V		RT		As Welded / 620°C±15°C /1h	920	1010	17	75		710	910	18	55	
Heat Treatment	R _{p0,2} MPa					R _m MPa	A ₅ (%)	Impact Energy (J) ISO-V												
		RT																		
As Welded / 620°C±15°C /1h	920	1010	17	75																
	710	910	18	55																
REDRYING TEMPERATURE	Not required																			
GAS ACCORDING EN 14175	M21																			