








CEWELD L-Ag18PL

TYPE	Special Copper-Silver-Phosphor brazing alloy.		
APPLICATIONS	Particularly recommended for sanitary and refrigerating installations, boilers, heat exchangers, tubing etc. Do not use in a sulphurous environment. For working temperatures up to 200 °C		
PROPERTIES	Self pickling on copper. Exceptional fluidity. It is very well suitable for the repair of the capillary losses of brazed joints with lower silver containing Phosphor-Copper Alloys. Ideal where the heat feeding is critical because of its low operating temperature. Flux/Paste: CEWELD Super-Flux		
CLASSIFICATION	AWS EN ISO F-nr	A 5.8: BCuP-8 17672: CuP 285 103	
SUITABLE FOR	Copper to Copper (without flux). Brass, Copper and Copper-Tin Alloys (with flux). Do not use in a sulphurous environment.		
APPROVALS	No Approvals Found		
WELDING POSITIONS	      		
TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)	Cu Rem.	Ag 17.8	P 6.5
ALL WELD MECHANICAL PROPERTIES	Heat Treatment As Welded /	R _{P0,2} MPa 250	R _m MPa A5 (%)
REDRYING TEMPERATURE	Not required		
GAS ACCORDING EN 14175			