



CEWELD CuSi3 Tig

TYPE	Copper-Silicon welding wire for Tig welding																		
APPLICATIONS	Welding thin plates and or galvanized plates in the car industry and also for cladding CuMn, CuSiMn and CuZn alloys. Suitable for cladding cast iron and un- and low alloyed steels. Examples: Automobile industry, art work, cladding on steel, cast iron and copper alloys etc.																		
PROPERTIES	<ul style="list-style-type: none"> • High quality alloyed copper wire for the Tig process (Mig brazing as well) • The weld metal is a Copper- Silicon bronze • Sound, pore free deposits on ferrous and non-ferrous base materials • Excellent corrosion resistance 																		
CLASSIFICATION	<table border="0"> <tr> <td>AWS</td> <td>A 5.7: ERCuSi-A</td> </tr> <tr> <td>EN ISO</td> <td>24373: Cu 6560 / CuSi3Mn1</td> </tr> <tr> <td>F-nr</td> <td>32</td> </tr> <tr> <td>W.Nr.</td> <td>2.1461</td> </tr> </table>	AWS	A 5.7: ERCuSi-A	EN ISO	24373: Cu 6560 / CuSi3Mn1	F-nr	32	W.Nr.	2.1461										
AWS	A 5.7: ERCuSi-A																		
EN ISO	24373: Cu 6560 / CuSi3Mn1																		
F-nr	32																		
W.Nr.	2.1461																		
SUITABLE FOR	<p>Welding thin steel plates and or galvanized plates in the car industry and also for cladding CuMn, CuSiMn and CuZn alloys. Suitable for cladding cast iron and un- and low alloyed steels.</p> <p>Sislicon Alloy:</p> <p>2.0220 - CuZn 5, 2.0230 - CuZn 10, 2.0240 - CuZn 15, 2.1322 - CuMg 0,4, 2.1323 - CuMg 0,7</p>																		
APPROVALS	No Approvals Found																		
WELDING POSITIONS																			
TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)	<table border="1" style="width: 100%; border-collapse: collapse; text-align: center;"> <tr> <td style="width: 33%;">Si</td> <td style="width: 33%;">Mn</td> <td style="width: 33%;">Cu</td> </tr> <tr> <td>2.95</td> <td>0.9</td> <td>Rem.</td> </tr> </table>	Si	Mn	Cu	2.95	0.9	Rem.												
Si	Mn	Cu																	
2.95	0.9	Rem.																	
ALL WELD MECHANICAL PROPERTIES	<table border="1" style="width: 100%; border-collapse: collapse; text-align: center;"> <tr> <td style="width: 15%;">Heat Treatment</td> <td style="width: 10%;">R_{P0,2}</td> <td style="width: 10%;">R_m</td> <td style="width: 10%;">A₅</td> <td style="width: 5%;"></td> <td style="width: 50%;">Hardness</td> </tr> <tr> <td></td> <td>MPa</td> <td>MPa</td> <td>(%)</td> <td></td> <td>Brinell Hardness</td> </tr> <tr> <td>As Welded /1h</td> <td></td> <td>350</td> <td></td> <td></td> <td>Avg. 80</td> </tr> </table>	Heat Treatment	R _{P0,2}	R _m	A ₅		Hardness		MPa	MPa	(%)		Brinell Hardness	As Welded /1h		350			Avg. 80
Heat Treatment	R _{P0,2}	R _m	A ₅		Hardness														
	MPa	MPa	(%)		Brinell Hardness														
As Welded /1h		350			Avg. 80														
REDRYING TEMPERATURE	Not required																		
GAS ACCORDING EN 14175	I1, I3																		



CEWELD CuSi3 Tig

CUSI3 TIG 1,6 X 1000MM	Type	KG/unit	EANCode
	Tube	5	8720663408310
CUSI3 TIG 2,0 X 1000MM	Type	KG/unit	EANCode
	Tube	5	8720663408327
CUSI3 TIG 2,4 X 1000MM	Type	KG/unit	EANCode
	Tube	5	8720663408334
CUSI3 TIG 3,0 X 1000MM	Type	KG/unit	EANCode
	Tube	5	8720663408341
CUSI3 TIG 3,2 X 1000MM	Type	KG/unit	EANCode
	Tube	5	8720663408358
CUSI3 TIG 4,0 X 1000MM	Type	KG/unit	EANCode
	Tube	5	8720663408365