

## CEWELD 4893 Kb (253MA)



TYPE Rutile coated electrode for heat resistant stainless steel SMAW welding.

APPLICATIONS Joining and cladding high heat resistant CrNi-steels of the same kind such as heat treatment

equipment and chemical installations.

PROPERTIES High corrosion resistance and excellent weldability on both AC and DC+. The weld deposit is scale

and oxidation resistant up to 950°C. Interpass temperature should be kept below 150°C.

CLASSIFICATION EN ISO 3581-A: E Z 23 10 N R 12

F-nr 5 FM 5 W.Nr. 1.4893

SUITABLE FOR 1.4828, 1.4829, 1.4893, 1.4835, 1.4818, 1.4825, 1.4826, 1.4832, 1.4891, 1.4893

X15CrNiSi 20-23, X12 CrNi 22-12, X8CrNiSiN21-11, X9CrNiSiNCe21-11-2

UNS S30815, AISI 309

(Avesta) alloy 253MA

APPROVALS No Approvals Found

WELDING POSITIONS

PA PB PC PD PF

TYPICAL CHEMICAL ANALYSIS OF WELD METAL

(%)

 C
 Si
 Mn
 Cr
 Ni
 Mo
 N

 0.1
 1
 0.97
 22
 11
 0.1
 0.1

ALL WELD MECHANICAL

**PROPERTIES** 

Heat	R <sub>P0,2</sub>	Rm	A5	
Treatment	MPa	MPa	(%)	
As Welded /	360	590	27	

REDRYING TEMPERATURE 300°C / 2 hr

**GAS ACCORDING EN 14175**