









CEWELD 4842 Kb

TYPE	Basic coated electrode for heat resistant stainless steels.(Type25 20, 310)						
APPLICATIONS	CEWELD® 4842 Kb is for the dissimilar welding of heat-resistant rolled, forged and cast steels. Common applications include industrial furnaces, annealing chambers, systems for treating molten salts and boiler parts as well as heat exchangers.						
PROPERTIES	CEWELD® 4842 Kb has good general oxidation resistance due to its high Cr content, especially at high temperatures. The alloy is fully austenitic and therefore sensitive to hot cracking in the 650-900°C temperature range. The temperature limits for use under intermittent oxidation depend on the frequency of cycling. In general, the alloy is resistant to scaling up to 1200°C. This alloy can withstand relatively strong thermal shocks and is therefore superior to type 309 L. Cold toughness down to - 196°C.						
CLASSIFICATION	AWS	A 5.4: E 310-15					
	EN ISO	3581-A: E 25 20 B 12					
	F-nr	5					
	FM	5					
	W.Nr.	~1.4842					
SUITABLE FOR	1.4823, 1.4826, 1.4828, 1.4832, 1.4840, 1.4841, 1.4846, 1.4848, 1.4837, 1.4710, 1.4713, 1.4724, 1.4726, 1.4742, 1.4745, 1.4762, 1.4845, 1.4740 X15CrNiSi25-21, X8CrNi25-21, X15CrNiSi20-12, GX15CrNi25-20, X40CrNi25-21, GX40CrNiSi22-10, X10CrAlSi7, X10CrAlSi13, X10CrAlSi18, X10CrAlSi25, GX30CrSi7, GX40CrSi17 AISI 305, 310, 314, ASTM A297 HF, A297 HJ						
APPROVALS	CE						
WELDING POSITIONS	<div>     </div>						
TYPICAL CHEMICAL ANALYSIS OF WELD METAL (%)	C	Si	Mn	P	S	Cr	Ni
	0.1	0.5	2	0.02	0.015	26	21
ALL WELD MECHANICAL PROPERTIES	Heat Treatment	R _{p0,2} MPa	R _m MPa	A ₅ (%)	RT	Impact Energy (J) ISO-V -196°C	
	As Welded /	380	570	30	75	37	
REDRYING TEMPERATURE	300°C / 2 hr						
GAS ACCORDING EN 14175							



CEWELD 4842 Kb

4842 KB 2,5 X 300MM

Type	KG/unit	EANCode
Can	2,5	8720663415776