



CEWELD NiCrMo 59 Tig

TYPE	Nickel-Chromium-Molybdenum based alloy for Tig welding																							
APPLICATIONS	Applications of NiCrMo 59 Tig in aggressively corrosive media include scrubbers for flue gas desulphurization (FGD), digesters and papermaking equipment, chemical process plants, corrosion resistant overlays and in severe offshore and petrochemical environments.																							
PROPERTIES	CEWELD NiCrMo 59 weld deposit composition of 59%Ni-23%Cr-16%Mo is designed to match the nickel base corrosion resistant alloy commonly known as alloy 59. The high level of Mo is similar to alloys C276 and C4 but performance in a wide range of more oxidizing media is significantly enhanced by increasing Cr to 23% in alloy 59. Total alloying exceeds the level typically present in alloy C22; it is therefore considered suitable for welding this group of alloys. Alloy 59 consumables also provide strong, tough Nb-free weld metal for dissimilar welds in Superaustenitic and Superduplex stainless steels or combinations of these with nickel base alloys. Some authorities do not allow or have discontinued use of 625 type consumables for such applications, where deleterious Nb-rich precipitates may form in diluted or partially mixed regions around the fusion boundary. Alloy C276 is possibly a more economic alternative depending on the required properties in this situation.																							
CLASSIFICATION	<table><tr><td>AWS</td><td>A 5.14: ERNiCrMo-13</td></tr><tr><td>EN ISO</td><td>18274: S Ni 6059(NiCr23Mo16)</td></tr><tr><td>F-nr</td><td>43</td></tr><tr><td>FM</td><td>6</td></tr><tr><td>W.Nr.</td><td>2.4607</td></tr></table>								AWS	A 5.14: ERNiCrMo-13	EN ISO	18274: S Ni 6059(NiCr23Mo16)	F-nr	43	FM	6	W.Nr.	2.4607						
AWS	A 5.14: ERNiCrMo-13																							
EN ISO	18274: S Ni 6059(NiCr23Mo16)																							
F-nr	43																							
FM	6																							
W.Nr.	2.4607																							
SUITABLE FOR	NiCr23Mo16Al, NiCr21Mo14W, NiCr23Mo16Al, NiMo16Cr15Ti, NiMo16Cr15W, NiMo16Cr16Ti, X2CrNiMnMoN 17-12-2, NiCr26MoW 2.4608, 2.4605, 2.4602, 2.4610, 2.4819, 2.4692, 1.4562, 1.4563, 1.4529, 1.4539, 1.4404 Duplex, Super-Duplex and Super-Austenitic Stainless steels, Nickel alloys such as UNS N06059 and N06022, INCONEL alloy C4, C-276, and INCONEL alloys 622, C22, 625, and 686 CPT, Alloy 31, Alloy 59, Alloy 33																							
APPROVALS	No Approvals Found																							
WELDING POSITIONS																								
TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)	<table><thead><tr><th>C</th><th>Si</th><th>Mn</th><th>Cr</th><th>Ni</th><th>Mo</th><th>Fe</th><th>Al</th></tr></thead><tbody><tr><td>0.008</td><td>0.09</td><td>0.2</td><td>23</td><td>65</td><td>16</td><td>1</td><td>0.3</td></tr></tbody></table>								C	Si	Mn	Cr	Ni	Mo	Fe	Al	0.008	0.09	0.2	23	65	16	1	0.3
C	Si	Mn	Cr	Ni	Mo	Fe	Al																	
0.008	0.09	0.2	23	65	16	1	0.3																	
ALL WELD MECHANICAL PROPERTIES	<table><thead><tr><th>Heat Treatment</th><th>R_{P0,2} MPa</th><th>R_m MPa</th><th>A5 (%)</th><th colspan="4">Impact Energy (J) ISO-V</th></tr></thead><tbody><tr><td>As Welded /</td><td>450</td><td>720</td><td>35</td><td colspan="4">-196°C 70 RT 100</td></tr></tbody></table>								Heat Treatment	R _{P0,2} MPa	R _m MPa	A5 (%)	Impact Energy (J) ISO-V				As Welded /	450	720	35	-196°C 70 RT 100			
Heat Treatment	R _{P0,2} MPa	R _m MPa	A5 (%)	Impact Energy (J) ISO-V																				
As Welded /	450	720	35	-196°C 70 RT 100																				
REDRYING TEMPERATURE	Not required																							
GAS ACCORDING EN 14175	I1																							



CEWELD NiCrMo 59 Tig

NICRMO 59 TIG 1,2 X
1000MM

Type	KG/unit	EANCode
Tube	5	8720663420381

NICRMO 59 TIG 1,6 X
1000MM

Type	KG/unit	EANCode
Tube	5	8720663420398

NICRMO 59 TIG 2,0 X
1000MM

Type	KG/unit	EANCode
Tube	5	8720663420404

NICRMO 59 TIG 2,4 X
1000MM

Type	KG/unit	EANCode
Tube	5	8720663420411

NICRMO 59 TIG 3,2 X
1000MM

Type	KG/unit	EANCode
Tube	5	8720663420428