



CEWELD Alloy C-276 Tig

TYPE	Nickel based Tig filler metal for welding similar NiCrMo alloys.										
APPLICATIONS	CEWELD Alloy C276 is used for welding materials of similar composition. This low carbon nickel-chromium-molybdenum filler metal can also be used for dissimilar welding between nickel base alloys and stainless steels, as well as for surfacing and cladding on low alloyed steels.										
PROPERTIES	Due to high molybdenum content this alloy offers excellent resistance too stress & corrosion cracking, pitting and crevice corrosion. High mechanical properties with excellent weldability.										
CLASSIFICATION	<table border="0"> <tr> <td>AWS</td> <td>A 5.14: ERNiCrMo-4</td> </tr> <tr> <td>EN ISO</td> <td>18274: S Ni 6276 (NiCr15Mo16Fe6W4)</td> </tr> <tr> <td>F-nr</td> <td>43</td> </tr> <tr> <td>FM</td> <td>6</td> </tr> <tr> <td>W.Nr.</td> <td>2.4887</td> </tr> </table>	AWS	A 5.14: ERNiCrMo-4	EN ISO	18274: S Ni 6276 (NiCr15Mo16Fe6W4)	F-nr	43	FM	6	W.Nr.	2.4887
AWS	A 5.14: ERNiCrMo-4										
EN ISO	18274: S Ni 6276 (NiCr15Mo16Fe6W4)										
F-nr	43										
FM	6										
W.Nr.	2.4887										

SUITABLE FOR **Alloy 276, Ni 6276 (NiCr15Mo16Fe6W4). 2.4886, 2.4887**
M.No: 1.5680, 1.5682, 2.4819, 2.4883
 NiMo16Cr15W, X12Ni5 / 12Ni19, X8Ni9, G-NiMo16Cr
 Alloy C4, Hastelloy C276, A494CW-12MW, A743 / A744CW-12M

APPROVALS No Approvals Found




TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)	C	Si	Mn	P	S	Cr	Ni	Mo	V	Fe	W	Co	Cu
	0.01	0.07	0.4	0.02	0.01	15.5	60	16	0.2	5	3.5	1	0.2

ALL WELD MECHANICAL PROPERTIES	Heat Treatment	R _{p0,2} MPa	R _m MPa	A5 (%)	Impact Energy (J) ISO-V RT
	As Welded /	470	740	32	100

REDRYING TEMPERATURE Not required

GAS ACCORDING EN 14175 I1



CEWELD Alloy C-276 Tig

ALLOY C-276 TIG 1,2
X1000MM

Type	KG/unit	EANCode
Tube	5	8720663419934

ALLOY C-276 TIG 1,6 X
914MM

Type	KG/unit	EANCode
Tube	4,54	8720663420008

ALLOY C-276 TIG 1,6
X1000MM

Type	KG/unit	EANCode
Tube	5	8720663419996

ALLOY C-276 TIG 2,0 X
1000MM

Type	KG/unit	EANCode
Tube	5	8720663420015

ALLOY C-276 TIG 2,0 X
914MM

Type	KG/unit	EANCode
Tube	4,54	8720663420022

ALLOY C-276 TIG 2,4 X
1000MM

Type	KG/unit	EANCode
Tube	5	8720663420039

ALLOY C-276 TIG 2,4 X
914MM

Type	KG/unit	EANCode
Tube	4,54	8720663420046

ALLOY C-276 TIG 3,2 X
1000MM

Type	KG/unit	EANCode
Tube	5	8720663420053

ALLOY C-276 TIG 3,2 X
914MM

Type	KG/unit	EANCode
Tube	4,54	8720663420060