



# CEWELD 2594 Tig (Super Duplex)

**certilas®** THE FILLER METAL SPECIALIST

TYPE	Tig filler metal for welding Super Duplex types of stainless steels.																																																																	
APPLICATIONS	<p>Welding austenitic-ferritic, stainless alloys of the 25% Cr, 7% Ni, 4% Mo, low C types. Welding wrought, forged or cast super duplex stainless steels for service in the as-welded Condition. Heterogeneous welding between super duplex stainless steels and dissimilar welds between other stainless and mild or low alloyed steels. The alloy is widely used in applications in which corrosion resistance is of the utmost importance. The pulp &amp; paper industry, offshore and gas industry are areas of interest.</p>																																																																	
PROPERTIES	2594 offers high intergranular-corrosion, pitting and stress-corrosion resistance with exceptional mechanical strength properties.																																																																	
CLASSIFICATION	<table> <tr> <td>AWS</td> <td colspan="10">A 5.9: ER2594</td> </tr> <tr> <td>EN ISO</td> <td colspan="10">14343-A: W 25 9 4 N L</td> </tr> <tr> <td>F-nr</td> <td colspan="10">6</td> </tr> <tr> <td>FM</td> <td colspan="10">5</td> </tr> <tr> <td>W.Nr.</td> <td colspan="10">1.4410</td> </tr> </table>											AWS	A 5.9: ER2594										EN ISO	14343-A: W 25 9 4 N L										F-nr	6										FM	5										W.Nr.	1.4410									
AWS	A 5.9: ER2594																																																																	
EN ISO	14343-A: W 25 9 4 N L																																																																	
F-nr	6																																																																	
FM	5																																																																	
W.Nr.	1.4410																																																																	
SUITABLE FOR	<p>1.4507, 1.4410, 1.4468, 1.4515, 1.4517, 1.4501, 1.4467, 1.4569, 1.4508  X2 CrNiMoCuN 25-6-3, X2 CrNiMoN 25-7-4, GX2 CrNiMoN 25-6-3, GX2 CrNiMoCuN 26-6-3, GX2 CrNiMoCuN 25-6-3-3, X2 CrNiMoCuWN 25-7-4, X2CrMnNiMoN26-5-4, X 2 CrNiMoN 26 7 4, GX2CrNiMoCuWN25-8-4  UNS S32520, S32550, S32750, S39274, S39277, S39553, S32760, J93380  Ferralium 255, SAF 2507, ZERON 100, UR 76 N, SM22Cr, SAF 2507, Alloy 2507, Alloy 2594, Super Duplex</p>																																																																	
APPROVALS	CE																																																																	
WELDING POSITIONS																																																																		
TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)	<table> <tr> <td>C</td><td>Si</td><td>Mn</td><td>P</td><td>S</td><td>Cr</td><td>Ni</td><td>Mo</td><td>N</td><td>W</td> </tr> <tr> <td>0.02</td><td>0.6</td><td>1.2</td><td>0.01</td><td>0.01</td><td>25</td><td>9</td><td>3.5</td><td>0.2</td><td>0.4</td> </tr> </table>											C	Si	Mn	P	S	Cr	Ni	Mo	N	W	0.02	0.6	1.2	0.01	0.01	25	9	3.5	0.2	0.4																																			
C	Si	Mn	P	S	Cr	Ni	Mo	N	W																																																									
0.02	0.6	1.2	0.01	0.01	25	9	3.5	0.2	0.4																																																									
ALL WELD MECHANICAL PROPERTIES	<table> <thead> <tr> <th>Heat Treatment</th><th>R<sub>P0,2</sub> MPa</th><th>R<sub>m</sub> MPa</th><th>A<sub>5</sub> (%)</th><th colspan="4">Impact Energy (J) ISO-V</th> </tr> </thead> <tbody> <tr> <td>As Welded /</td><td>620</td><td>780</td><td>26</td><td>-20°C</td><td>60</td><td>-40°C</td><td>50</td> </tr> </tbody> </table>											Heat Treatment	R <sub>P0,2</sub> MPa	R <sub>m</sub> MPa	A <sub>5</sub> (%)	Impact Energy (J) ISO-V				As Welded /	620	780	26	-20°C	60	-40°C	50																																							
Heat Treatment	R <sub>P0,2</sub> MPa	R <sub>m</sub> MPa	A <sub>5</sub> (%)	Impact Energy (J) ISO-V																																																														
As Welded /	620	780	26	-20°C	60	-40°C	50																																																											
REDRYING TEMPERATURE	Not required																																																																	
GAS ACCORDING EN 14175	I1																																																																	