



CEWELD SG Ni3,5 Tig

TYPE	Solid Tig welding wire for extra low temperature applications.
APPLICATIONS	Used in petrochemical industry where it finds applications in construction of cryogenic plant and associated pipework, in the manufacture, storage and distribution of volatile liquids and liquefied gases.
PROPERTIES	Excelent impact properties at subzero temperatures down to -80°C.
CLASSIFICATION	AWS A 5.28: ER 80S-Ni3
SUITABLE FOR	ASTM A 203 Gr D, E, F - A 333 Gr 3 - A 350 Gr LF3 - A 352 Gr LC3 EN (BS 1501 Gr 503 - BS 1503 Gr 503 - BS 1504 Gr 503 LT60)
APPROVALS	No Approvals Found
WELDING POSITIONS	
REDRYING TEMPERATURE	Not required
GAS ACCORDING EN 14175	



CEWELD SG Ni3,5 Tig

SG NI3,5 TIG 2,4 X 1000MM

Type	KG/unit	EANCode
Tube	5	8720663406149

SG NI3,5 TIG 3,2 X 1000MM

Type	KG/unit	EANCode
Tube	5	8720663406156