



CEWELD SG Ni1 Tig

TYPE	Tig - rod for fine grain steels and cold-tough steels. (G 50 6, 80S- Ni1)															
APPLICATIONS	CEWELD® SG Ni1 Tig fulfills offshore requirements at working temperatures down to -60 °C. Areas of application are: for cranes, ships, drilling rigs, platforms, pipelines for NACE requirements, boilers, pipes, etc.															
PROPERTIES	CEWELD® SG Ni1 Tig have excellent impact properties at low temperatures due to the addition of Nickel and increased yield strenght above 500 MPa.															
CLASSIFICATION	AWS	A 5.28: ER 80S-Ni1														
	EN ISO	636-A: W 46 6 3Ni														
	F-nr	6														
	FM	1														
SUITABLE FOR	ReH ≤ 500 MPa ISO 15608: 1.2 (275 < ReH < 360 MPa), 1.3 (ReH > 360 MPa < 500 MPa) 1.8900, 1.8901, 1.8902, 1.8903, 1.8905, 1.8907, 1.8910, 1.8912, 1.8915, 1.8917, 1.8930, 1.8932, 1.8935, 1.8937, 1.8970, 1.8971, 1.8972, 1.8973, 1.8975 S460N, S420N, S460NL, P460N, StE 420, StE 460, StE 500, TStE 380, S420NL, P460NL1, P420NH, P460NH, TStE 420, TStE 460, TStE 500, WStE 380, WStE 420, WStE 460, WStE 500, StE 385.7, StE 385.7 TM, StE 415, L485ME, 11MnNi5-3, 13MnNi6-3 ASTM A 203 Gr. D, E; A 350 Gr. LF1, LF2, LF3; A 420 Gr. WPL3, WPL6; A 516 Gr. 60, 65, 70; A 572 Gr. 42, 50, 55, 60, 65; A 633 Gr. A, D, E; A 662 Gr. A, B, C; A 707 Gr. L1, L2, L3; A 738 Gr. A; A 841 A, B, C; API 5 L X52, X60, X65, X52Q, X60Q, X65Q															
APPROVALS	CE															
WELDING POSITIONS																
TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)	<table border="1" style="width: 100%; border-collapse: collapse; text-align: center;"> <thead> <tr> <th>C</th> <th>Si</th> <th>Mn</th> <th>P</th> <th>S</th> <th>Ni</th> </tr> </thead> <tbody> <tr> <td>0.08</td> <td>0.5</td> <td>1.05</td> <td>0.007</td> <td>0.015</td> <td>0.9</td> </tr> </tbody> </table>		C	Si	Mn	P	S	Ni	0.08	0.5	1.05	0.007	0.015	0.9		
C	Si	Mn	P	S	Ni											
0.08	0.5	1.05	0.007	0.015	0.9											
ALL WELD MECHANICAL PROPERTIES	<table border="1" style="width: 100%; border-collapse: collapse; text-align: center;"> <thead> <tr> <th rowspan="2">Heat Treatment</th> <th rowspan="2">R_{P0,2} MPa</th> <th rowspan="2">R_m MPa</th> <th rowspan="2">A₅ (%)</th> <th colspan="2">Impact Energy (J) ISO-V</th> </tr> <tr> <th>-40°C</th> <th>-60°C</th> </tr> </thead> <tbody> <tr> <td>As Welded /</td> <td>500</td> <td>570</td> <td>24</td> <td>70</td> <td>55</td> </tr> </tbody> </table>		Heat Treatment	R _{P0,2} MPa	R _m MPa	A ₅ (%)	Impact Energy (J) ISO-V		-40°C	-60°C	As Welded /	500	570	24	70	55
Heat Treatment	R _{P0,2} MPa	R _m MPa					A ₅ (%)	Impact Energy (J) ISO-V								
			-40°C	-60°C												
As Welded /	500	570	24	70	55											
REDRYING TEMPERATURE	Not required															
GAS ACCORDING EN 14175	I1															



CEWELD SG Ni1 Tig

SG NI1 TIG 1,6 X 1000MM	Type	KG/unit	EANCode
	Tube	5	8720663405692
SG NI1 TIG 2,0 X 1000MM	Type	KG/unit	EANCode
	Tube	5	8720663405708
SG NI1 TIG 2,4 X 1000MM	Type	KG/unit	EANCode
	Tube	5	8720663405722
SG NI1 TIG 3,2 X 1000MM	Type	KG/unit	EANCode
	Tube	5	8720663405739