



# CEWELD AA R460

TYPE	Seamless micro-alloyed rutile flux-cored wire for CO2 and M21. ( Type E 71 T1, T 46 4 )														
APPLICATIONS	Fully sealed cored wire for single or multi-pass welding of carbon, carbon-manganese steels and fine-grain structural steels using 100% CO2 and Mixgas M21 (Ar/CO2) shielding gas. Shipbuilding, Steel structures, Offshore structures, Pipelines, Non-alloy and fine grain steels, Vessels, General fabrication, Heavy equipment, Single and multi-pass welding														
PROPERTIES	Excellent weld puddle manipulation due to fast freezing slag, superior out-of-position welding also at higher currents. Using temperature up to -40°C. Particularly suited for MAG-orbital welding and all-position welding on ceramic backing. Extreme low spatter loss, easy slag removal and hydrogen content below 3 ml/100g. even after long unconditioned storage.														
CLASSIFICATION	<table border="0"> <tr> <td>AWS</td> <td>A 5.20: E71T-1M-J H4</td> </tr> <tr> <td>AWS</td> <td>A 5.36: E71T1-M21A4-CS1-H4</td> </tr> <tr> <td>AWS</td> <td>A 5.36: E71T1-1CA0-CS1-H4</td> </tr> <tr> <td>EN ISO</td> <td>17632-A: T 46 4 P M21 1 H5</td> </tr> <tr> <td>EN ISO</td> <td>17632-A: T 42 2 P C1 1 H5</td> </tr> <tr> <td>F-nr</td> <td>6</td> </tr> <tr> <td>FM</td> <td>1</td> </tr> </table>	AWS	A 5.20: E71T-1M-J H4	AWS	A 5.36: E71T1-M21A4-CS1-H4	AWS	A 5.36: E71T1-1CA0-CS1-H4	EN ISO	17632-A: T 46 4 P M21 1 H5	EN ISO	17632-A: T 42 2 P C1 1 H5	F-nr	6	FM	1
AWS	A 5.20: E71T-1M-J H4														
AWS	A 5.36: E71T1-M21A4-CS1-H4														
AWS	A 5.36: E71T1-1CA0-CS1-H4														
EN ISO	17632-A: T 46 4 P M21 1 H5														
EN ISO	17632-A: T 42 2 P C1 1 H5														
F-nr	6														
FM	1														
SUITABLE FOR	<p><b>ReH ≤ 460 MPa (67 ksi) ISO 15608: 1.1, 1.2, 1.3, 2.1, 3.1 (ReH max. 485 MPa)</b>            1.5637, 1.6217, 1.6228, 1.0044-1.09821.0035 - 1.0570, 1.0345, 1.0425, 1.0481, 1.0308 - 1.0581, 1.0307 - 1.0582, 1.0440, 1.0472, 1.0475, 1.0416 to 1.0551            10Ni14, 12Ni14, 13MnNi6-3, 15NiMn6,            S235JR-S355JR, S235JO-S355JO, S450JO, S235J2-S355J2, S275N-S460N, S275M-S460M,            P235GH-P355GH, P275NL1-P460NL1, P215NL, P265NL, P355N, P285NH-P460NH, P195TR1-P265TR1, P195TR2-P265TR2, P195GH-P265GH, L245NB-L415NB, L450QB, L245MB-L450MB, GE200-GE240,            A, B, D, E, A 32-E 36            ASTM A 106 Gr. A, B, C; A 181 Gr. 60, 70; A 283 Gr. A, C; A 285 Gr. A, B, C; A 350 Gr. LF1; A 414 Gr. A, B, C, D, E, F, G; A 501 Gr. B; A 513 Gr. 1018; A 516 Gr. 55, 60, 65, 70; A 573 Gr. 58, 65, 70; A 588 Gr. A, B; A 633 Gr. C, E; A 662 Gr. B; A 711 Gr. 1013; A 841 Gr. A; API 5 L Gr. B, X42, X52, X56, X60, X65            Domex 315-460MC,MC Plus, ML</p>														
APPROVALS	CE TÜV (12704) Lloyds DNV														
WELDING POSITIONS															
TYPICAL CHEMICAL ANALYSIS OF WELD METAL (%)	<table border="1"> <thead> <tr> <th>C</th> <th>Si</th> <th>Mn</th> <th>P</th> <th>S</th> </tr> </thead> <tbody> <tr> <td>0.08</td> <td>0.5</td> <td>1.3</td> <td>0.015</td> <td>0.015</td> </tr> </tbody> </table>	C	Si	Mn	P	S	0.08	0.5	1.3	0.015	0.015				
C	Si	Mn	P	S											
0.08	0.5	1.3	0.015	0.015											
ALL WELD MECHANICAL PROPERTIES	<table border="1"> <thead> <tr> <th rowspan="2">Heat Treatment</th> <th rowspan="2">R<sub>P0,2</sub> MPa</th> <th rowspan="2">R<sub>m</sub> MPa</th> <th rowspan="2">A<sub>5</sub> (%)</th> <th colspan="2">Impact Energy (J) ISO-V</th> </tr> <tr> <th>-20°C</th> <th>-40°C</th> </tr> </thead> <tbody> <tr> <td>As Welded /</td> <td>490</td> <td>580</td> <td>25</td> <td>90</td> <td>70</td> </tr> </tbody> </table>	Heat Treatment	R <sub>P0,2</sub> MPa	R <sub>m</sub> MPa	A <sub>5</sub> (%)	Impact Energy (J) ISO-V		-20°C	-40°C	As Welded /	490	580	25	90	70
Heat Treatment	R <sub>P0,2</sub> MPa					R <sub>m</sub> MPa	A <sub>5</sub> (%)	Impact Energy (J) ISO-V							
		-20°C	-40°C												
As Welded /	490	580	25	90	70										
REDRYING TEMPERATURE	Not required														
GAS ACCORDING EN 14175	M21, C1														



# CEWELD AA R460

## AA R460 1,0MM

Type	KG/unit	EANCode
D-200	20 (4x5)	8720663423597
K-300	16	8720663423610

## AA R460 1,2MM

Type	KG/unit	EANCode
BS-300	16	8720663423627
D-200	20 (4x5)	8720663423603

## AA R460 1,4MM

Type	KG/unit	EANCode
K-300	16	8720663423634

## AA R460 1,6MM

Type	KG/unit	EANCode
K-300	16	8720663423641