



CEWELD AA B500

TYPE	Basic seamless micro alloyed flux cored welding wire																								
APPLICATIONS	Pressure vessels, steam boilers, riser pipes, low temperature requirements, high demanding and stressed constructions that needs post weld heat treatment.																								
PROPERTIES	AA B500 is a seamless high basic flux cored wire for extreme offshore requirements at sub zero temperatures down to - 60 °C (-80°C). Excellent welding properties. Therefore, suitable for the economic processing of high-strength, low temperature fine-grained structural steels with Rp0,2 > 500 MPa. Low hydrogen content HD< 3 ml/100g even after long storage.																								
CLASSIFICATION	<table border="0"> <tr> <td>AWS</td> <td>A 5.29: E80T5-Ni</td> </tr> <tr> <td>AWS</td> <td>A 5.36: E80T5-M21A8-Ni1-H4</td> </tr> <tr> <td>EN ISO</td> <td>17632-A: T 50 6 1 Ni B M21 3 H5</td> </tr> <tr> <td>F-nr</td> <td>6</td> </tr> <tr> <td>FM</td> <td>1</td> </tr> </table>	AWS	A 5.29: E80T5-Ni	AWS	A 5.36: E80T5-M21A8-Ni1-H4	EN ISO	17632-A: T 50 6 1 Ni B M21 3 H5	F-nr	6	FM	1														
AWS	A 5.29: E80T5-Ni																								
AWS	A 5.36: E80T5-M21A8-Ni1-H4																								
EN ISO	17632-A: T 50 6 1 Ni B M21 3 H5																								
F-nr	6																								
FM	1																								
SUITABLE FOR	<p>Reh ≤ 500 MPa, ISO 15608: 1.3, 2.1, 2.3</p> <p>S355JR, S355J0, S355J2, S450J0, S355N-S460N, S355NL-S460NL, S355M-S460M, S355ML-S460ML, S460Q, S500Q, S460QL, S500QL, S460QL1, S500QL1, P355GH, P355NH, P420NH, P460NH, P355N-P460N, P355NH-P460NH, P355NL1-P460NL1, P355NL2- P460NL2, L245NB- L415NB, L245MB-L485MB, L360QB-L485QB</p> <p>ASTM A 350 Gr. LF2; A 516 Gr. 65, 70; A 572 Gr. 42, 50, 60, 65; A 573 Gr. 70; A 588 Gr. B, C, K; A 633 Gr. A, C, D, E; A 662 Gr. B, C; A 678 Gr. B; A 707 Gr. L2, L3; A 841 Gr. A, B, C;</p> <p>API 5 L X42, X52, X60, X65, X70, X52Q, X60Q, X65Q, X70Q,</p> <p>aldur 500Q, aldur 500QL, aldur 500QL1, Domex 420 -500 MC,MC Plus, ML, Dilimax 460 -500,</p>																								
APPROVALS	CE																								
WELDING POSITIONS																									
TYPICAL CHEMICAL ANALYSIS OF WELD METAL (%)	<table border="1"> <thead> <tr> <th>C</th> <th>Si</th> <th>Mn</th> <th>P</th> <th>S</th> <th>Ni</th> </tr> </thead> <tbody> <tr> <td>0.08</td> <td>0.7</td> <td>1.5</td> <td>0.015</td> <td>0.015</td> <td>0.9</td> </tr> </tbody> </table>	C	Si	Mn	P	S	Ni	0.08	0.7	1.5	0.015	0.015	0.9												
C	Si	Mn	P	S	Ni																				
0.08	0.7	1.5	0.015	0.015	0.9																				
ALL WELD MECHANICAL PROPERTIES	<table border="1"> <thead> <tr> <th rowspan="2">Heat Treatment</th> <th rowspan="2">Rp0,2 MPa</th> <th rowspan="2">Rm MPa</th> <th rowspan="2">A5 (%)</th> <th colspan="3">Impact Energy (J) ISO-V</th> </tr> <tr> <th>-80°C</th> <th>-40°C</th> <th>-60°C</th> </tr> </thead> <tbody> <tr> <td>As Welded /</td> <td>540</td> <td>620</td> <td>23</td> <td>50</td> <td></td> <td></td> </tr> <tr> <td>570°C- 620°C /1h</td> <td>560</td> <td>645</td> <td>26</td> <td>70</td> <td>120</td> <td>95</td> </tr> </tbody> </table>	Heat Treatment	Rp0,2 MPa	Rm MPa	A5 (%)	Impact Energy (J) ISO-V			-80°C	-40°C	-60°C	As Welded /	540	620	23	50			570°C- 620°C /1h	560	645	26	70	120	95
Heat Treatment	Rp0,2 MPa					Rm MPa	A5 (%)	Impact Energy (J) ISO-V																	
		-80°C	-40°C	-60°C																					
As Welded /	540	620	23	50																					
570°C- 620°C /1h	560	645	26	70	120	95																			
REDRYING TEMPERATURE	Not required																								
GAS ACCORDING EN 14175	M21																								



CEWELD AA B500

AA B500 1,2MM

Type	KG/unit	EANCode
K-300	16	8720663405371