





4.8

TYPE Fluxcored wire for hardfacing with exceptional hardness.

APPLICATIONS Hardfacing wire against heavy wear with excelent abrasion resistance against sand and minerals.

PROPERTIES Extreme good wear resistance even with thin coating thickness due to a high amount of Borium

carbides. A extreme high hardness is already achieved in the first layer. The weld deposit will show release cracks to offer better bonding strenght with the base metal. More than 1 layer should not be deposited. A Buffer layer is recommended in case of sensitive base material or old unknown layers. OA 67 NiBo can be welded without using protective gas (open arc) but is also available as Gas

shielded version.

CLASSIFICATION EN ISO 14700: T Fe13

DIN 8555: MF 2-GF-70-G

SUITABLE FOR Mining and steel mills, conveyor chains, agriculture, construction, mixer blades, paddles, cement

pumps, screw conveyers, sintering lines, earth moving equipment etc.

APPROVALS No Approvals Found

WELDING POSITIONS



0.5

TYPICAL CHEMICAL ANALYSIS OF WELD METAL

(%)

ALL WELD MECHANICAL PROPERTIES

Heat	R _{P0,2}	Rm	A5	Hardness
Treatment	MPa	MPa	(%)	Rockwell C
As Welded /				Avg. 67

Mn

REDRYING TEMPERATURE 140

140°C / 24 hr

GAS ACCORDING EN 14175