









CEWELD ERTi-1 Tig

TYPE	Solid Titanium welding wire Grade 1 (purest grade)					
APPLICATIONS	CEWELD ERTi-1 Grade 1 is the lowest strength unalloyed (or Commercially Pure-CP) grade. Grade 1 is used in applications where ductility is paramount, such as explosive cladding, loose linings, expanded metal, and deep drawing applications. It is also used in electrolytic applications like coated anode substrates for production of chlorine and sodium chlorate.					
PROPERTIES	The weld deposit is ductile and offers excellent corrosion resistance in oxidizing environments. The purity and corrosion resistance makes the alloy a preferred choice in many applications to prevent or solve problems. The wire is cleaned in a very special way to obtain porosity free and a ductile weld deposits.					
CLASSIFICATION	AWS	A 5.16: ERTi-1				
	EN ISO	24034: S Ti 0100 / Ti99,8				
	F-nr	51				
	W.Nr.	3.7026				
SUITABLE FOR	3.7025, ~3.7035, ~3.7065 Titan Grade 1, ER Ti-1 is the purest grade and is suitable for welding Titanium grade 1, 2, 3 and 4. With the restriction that the mechanical properties are much less than Grade 2, 3 and 4.					
APPROVALS	No Approvals Found					
WELDING POSITIONS	<div>      </div>					
TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)	C	H	N	O	Fe	Ti
	0.02	0.003	0.01	0.03	0.02	Rem.
ALL WELD MECHANICAL PROPERTIES	Heat Treatment	R _{P0,2} MPa	R _m MPa	A5 (%)		
	As Welded /	250	320	24		
REDRYING TEMPERATURE	Not required					
GAS ACCORDING EN 14175	I1					



CEWELD ERTi-1 Tig

ERTI-1 TIG 1,2 X 1000MM

Type	KG/unit	EANCode
Tube	2,5	8720663406330

ERTI-1 TIG 1,6 X 1000MM

Type	KG/unit	EANCode
Tube	2,5	8720663406347

ERTI-1 TIG 2,0 X 1000MM

Type	KG/unit	EANCode
Tube	2,5	8720663406354

ERTI-1 TIG 2,4 X 1000MM

Type	KG/unit	EANCode
Tube	2,5	8720663406361