





TYPE Solid wire for submerged arc welding with 17% Cr.

APPLICATIONS Cladding seats, valves, wheels, shafts etc.

PROPERTIES Submerged arc welding wire to be used with fused flux FL 880 or agglomerated flux FL 838 flux

with excellent welding properties. Stainless deposit with low carbon content. Low heat input is recommended to avoid pronounced grain coarsening. Absence of stabilization means that this steel is distinctly vulnerable to sensitization phenomenon during welding, even though martensite hogs a

great amount of carbon and nitrogen.

CLASSIFICATION AWS A 5.9: ER430

EN ISO 14343-A: S 17

F-nr 6 FM 5 W.Nr. 1.4016

Si

SUITABLE FOR 1.4000, 1.4002, 1.4016, 1.4057, 1.4113, 1.4057, 1.4059, 1.4332, 1.4502, 1.4509, 1.4510, 1.4511,

 $1.4512,\, 1.4520,\, 1.4523,\, 1.4712,\, 1.4713,\, 1.4724,\, 1.4740,\, 1.4741,\, 1.4742,\, 1.4842,\, 1.4744,\, 1.4742,\, 1.4842,\, 1$

X7Cr14, X12Cr13, X17CrNi16-2, X6Cr13, X6CrAl13, X6Cr17, X17CrNi16-2, X2CrTiNb18, X3CrTi17,

X3CrNb17, X2CrTi12, X2CrTi17, X10CrSi6, X10CrAlSi7, X10CrAlSi13, X10CrAlSi18

UNS \$40300, \$40500, \$40900, \$41000, \$42900, \$43000, \$43035, \$43036, \$43100, \$44200

AISI 403, 405, 409, 410, 429, 430, 430Cb, 430Ti, 439, 431, 442

Mn

APPROVALS No Approvals Found

WELDING POSITIONS



TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)

ALL WELD MECHANICAL

PROPERTIES

0.02	0.4	0.46	0.02	0.01	17	0.3	0.3

S

Cr

 Heat
 R_{P0,2}
 Rm
 A5
 Hardness

 Treatment
 MPa
 MPa
 (%)
 Brinell Hardness

 As Welded /
 Avg. 250

REDRYING TEMPERATURE Not required

GAS ACCORDING EN 14175

Mο





CEWELD SA 430

 SA 430 3,2MM
 Type
 KG/unit
 EANCode

 K-415
 25
 8720663412072