

CEWELD 2594 Super Duplex

TYPE 2594 Super Duplex stainless steel Mig/Mag GMAW welding wire for Zeron 100, Uranus 76, SAF 2507 and similar alloys

APPLICATIONS CEWELD® 2594 Super Duplex was specially developed for welding super duplex ferritic-austenitic steels (25% Cr, 9% Ni, 4% Mo). It is characterized by high tensile strength and toughness as well as excellent resistance to stress corrosion cracking, pitting, and intergranular corrosion. The operating temperature range is between -50 °C and 250 °C. The alloy is often used in applications where corrosion resistance is of paramount importance. The pulp and paper industry, as well as the offshore and gas industries, are areas of interest.

PROPERTIES CEWELD® 2594 Super Duplex exhibits high resistance to intergranular corrosion, pitting, and stress corrosion cracking, and has exceptional mechanical strength properties. Particularly in H2S-containing environments. Suitable for operating temperatures from -40°C to +220°C.

CLASSIFICATION

AWS	A 5.9: ER2594
EN ISO	14343-A: G 25 9 4 N L
F-nr	6
FM	5
W.Nr.	1.4410

SUITABLE FOR ISO 15608: 10.2-10.3 Austenitic > 24 % Cr ≤ 4% Ni, DUPLEX 2594, 25%Cr 9%Ni 4%Mo
 1.4410, 1.4467, 1.4468, 1.4501, 1.4507, 1.4508, 1.4515, 1.4517, 1.4569
 X2 CrNiMoCuN 25-6-3, X2 CrNiMoN 25-7-4, GX2 CrNiMoN 25-6-3, GX2 CrNiMoCuN 26-6-3, GX2 CrNiMoCuN 25-6-3-3, X2 CrNiMoCuWN 25-7-4, X2CrMnNiMoN26-5-4, X 2 CrNiMoN 26 7 4, GX2CrNiMoCuWN25-8-4
 UNS S32520, S32550, S32750, S39274, S39277, S39553, S32760, J93380, J93404
 Ferralium 255, SAF 2507, ZERON 100, UR 76 N, SM22Cr, SAF 2507, Alloy 2507, Alloy 2594, Super Duplex, Uranus® 47N

APPROVALS CE

WELDING POSITIONS

TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)


C	Si	Mn	Cr	Ni	Mo	N	W
0.02	0.6	1.2	25	9	3.5	0.2	0.4

ALL WELD MECHANICAL PROPERTIES

Heat Treatment	R _{p0,2} MPa	R _m MPa	A ₅ (%)	Impact Energy (J) ISO-V	
				-20°C	-40°C
As Welded /	700	900	27	65	55

REDRYING TEMPERATURE Not required

GAS ACCORDING EN 14175 M13, M12



CEWELD 2594 Super Duplex

2594 SUPER DUPLEX 0,8MM	Type	KG/unit	EANCode
	BS-300	15	8720663414694
2594 SUPER DUPLEX 1,0MM	Type	KG/unit	EANCode
	BS-300	15	8720663414700
2594 SUPER DUPLEX 1,2MM	Type	KG/unit	EANCode
	BS-300	15	8720663414717