



# CEWELD AA 904 LP

TYPE	Rutile fluxcored austenitic filler metal with excelent corrosion resistance																		
APPLICATIONS	Tanks and process vessels, Piping systems, agitators, rotors, cast pumps and valves for use in the fertilizer, phosphoric,sulphuric and acetic acid plants																		
PROPERTIES	The Ceweld AA 904LP is used for welding materials of similar chemical composition which are used for fabrication of equipment and vessels for handling of sulfuric acid and many chloride containing media. This fluxcored wire may also find applications for joining Type 317L material where improved corrosion resistance in specific media is needed. In order to reduce the propensity for fissuring and hot cracking, the low melting constituents such as carbon, silicon, and phosphorus are controlled to lower levels in this alloy. Suitable in all positions.																		
CLASSIFICATION	<table border="0"> <tr> <td>AWS</td> <td>A 5.22: ~385T1-4</td> </tr> <tr> <td>EN ISO</td> <td>17633-A: T 20 25 5 Cu N L P M21 2</td> </tr> <tr> <td>F-nr</td> <td>6</td> </tr> <tr> <td>FM</td> <td>5</td> </tr> <tr> <td>W.Nr.</td> <td>1.4539</td> </tr> </table>	AWS	A 5.22: ~385T1-4	EN ISO	17633-A: T 20 25 5 Cu N L P M21 2	F-nr	6	FM	5	W.Nr.	1.4539								
AWS	A 5.22: ~385T1-4																		
EN ISO	17633-A: T 20 25 5 Cu N L P M21 2																		
F-nr	6																		
FM	5																		
W.Nr.	1.4539																		
SUITABLE FOR	<p><b>1.4539 / 904L CrNiMoCu / 20 25 5 Cu L</b>            1.4465, 1.4500, 1.4505, 1.4506, 1.4519, 1.4531, 1.4536, 1.4537, 1.4538, 1.4539, 1.4573, 1.4585, 1.4586            X1CrNiMoN25-25-2, X1NiCrMoCu 25-20-5, X1CrNiMoCuN 25-25-5, X2NiCrMoCuN25-20-5, X2NiCrMoCuN20-18, X4NiCrMoCuNb 20-18-2, X5NiCrMoCuTi20-18, X5NiCrMoCuNb22-18            ASTM A182,            UNS N08904, S31726            Uranus B6, AISI 904L, Z2NCDU25-20,</p>																		
APPROVALS	CE																		
WELDING POSITIONS																			
TYPICAL CHEMICAL ANALYSIS OF WELD METAL (%)	<table border="1" style="width: 100%; border-collapse: collapse; text-align: center;"> <thead> <tr> <th>C</th> <th>Si</th> <th>Mn</th> <th>P</th> <th>Cr</th> <th>Ni</th> <th>Mo</th> <th>N</th> <th>Cu</th> </tr> </thead> <tbody> <tr> <td>0.03</td> <td>0.65</td> <td>1.55</td> <td>0.025</td> <td>21</td> <td>25.5</td> <td>5</td> <td>0.15</td> <td>1.35</td> </tr> </tbody> </table>	C	Si	Mn	P	Cr	Ni	Mo	N	Cu	0.03	0.65	1.55	0.025	21	25.5	5	0.15	1.35
C	Si	Mn	P	Cr	Ni	Mo	N	Cu											
0.03	0.65	1.55	0.025	21	25.5	5	0.15	1.35											
ALL WELD MECHANICAL PROPERTIES	<table border="1" style="width: 100%; border-collapse: collapse; text-align: center;"> <thead> <tr> <th rowspan="2">Heat Treatment</th> <th rowspan="2">R<sub>P0,2</sub> MPa</th> <th rowspan="2">R<sub>m</sub> MPa</th> <th rowspan="2">A<sub>5</sub> (%)</th> <th colspan="2">Impact Energy (J) ISO-V</th> </tr> <tr> <th colspan="2">-196°C</th> </tr> </thead> <tbody> <tr> <td>As Welded /</td> <td>425</td> <td>665</td> <td>35</td> <td colspan="2">60</td> </tr> </tbody> </table>	Heat Treatment	R <sub>P0,2</sub> MPa	R <sub>m</sub> MPa	A <sub>5</sub> (%)	Impact Energy (J) ISO-V		-196°C		As Welded /	425	665	35	60					
Heat Treatment	R <sub>P0,2</sub> MPa					R <sub>m</sub> MPa	A <sub>5</sub> (%)	Impact Energy (J) ISO-V											
		-196°C																	
As Welded /	425	665	35	60															
REDRYING TEMPERATURE	140°C / 24 hr																		
GAS ACCORDING EN 14175	M21																		



# CEWELD AA 904 LP

AA 904 LP 1,2MM

Type	KG/unit	EANCode
BS-300	15	8720663413734