



CEWELD AA 317L

TYPE	AA 317L is a rutile flux cored wire with easy removable slag	
APPLICATIONS	Boilers, shipbuilding, machinery, offshore application, foundries, chemical industry, orbital tube welding etc.	
PROPERTIES	AA 317L is a rutile flux cored wire with easy removable slag support for high productivity welding. Smooth drop transfer and stable arc with no spatter losses. Excellent weld metal quality and X-ray soundness.	
CLASSIFICATION	AWS	A 5.22: E317LT0-1
	AWS	A 5.22: E317LT0-4
	EN ISO	17633-A: TZ 19 13 4 L R M21 3
	F-nr	6
	FM	5
	W.Nr.	1.4440

SUITABLE FOR Designed for joining corrosion resistant CrNiMoN steel as well as for austenitic-ferritic joints.
ISO 15608: 8.1 Austenitic ≤ 19 % Cr , TÜV 1000: Gr. 26, 27, 28
 1.4429, 1.4434, 1.4435, 1.4436, 1.4438, 1.4439, 1.4453, 1.4583,
 X2CrNiMoN 17 13 5, X2CrNiMoN 17 13 3, X2CrNiMo 18 15 4, X10CrNiMoNb 18 12, X2CrNiMoN17-13-3, X2CrNiMoN18-12-4, X2CrNiMo18-14-3, X3CrNiMnMoN19-16
 UNS S31600, S31653, S31703, S31726, S31753
 AISI 316Cb, 316L, 316LN, 317L, 317LN, 317LMN

APPROVALS CE

WELDING POSITIONS



TYPICAL CHEMICAL ANALYSIS OF WELD METAL (%)


C	Si	Mn	P	Cr	Ni	Mo	S	FN	FS	FNW
0.03	0.7	1.6	0.025	19	13.5	3.5	0.025	11.6	0.2	8.7

ALL WELD MECHANICAL PROPERTIES

Heat Treatment	R _{p0,2} MPa	R _m MPa	A ₅ (%)	Impact Energy (J) ISO-V -40°C
As Welded /	360	550	26	40

REDRYING TEMPERATURE 140°C / 24 hr

GAS ACCORDING EN 14175 M21



CEWELD AA 317L

AA 317L 1,2MM

Type	KG/unit	EANCode
BS-300	15	8720663413581