



CEWELD SA 308L strip

TYPE	Stainless steel strip for ESW. (Type 308L, 19 9 L)							
APPLICATIONS	Cladding surfaces							
PROPERTIES	Strip with 19Cr/9Ni composition, ESW process has very low dilution so in the first layer you almost reach the chemical composition. Flux FL 860 ESH can be used.							
CLASSIFICATION	AWS	A 5.9: EQ308L						
	EN ISO	14343-A: B 19 9 L						
	FM	1.4316						
SUITABLE FOR	ISO 15608: 8.1 Austenit ≤ 19 % Cr 9% Ni, TÜV 1000: Gr. 21 - 22 (29 max.350°C), 1.4301, 1.4306, 1.4307, 1.4308, 1.4311, 1.4312, 1.6900, 1.6901, 1.6902, 1.6903, 1.9606, 1.4541, 1.4546, 1.4550 X 5 CrNi 18 10, X 2 CrNi 19 11, X 5 CrNi 18 9, G-X 6 CrNi 18 9, X 12 CrNi 18 9, G-X 8 CrNi 18 10, X 6 CrNi 18 10, X 10 CrNiTi 18 10, X 5 CrNi 18 10 AISI 304, 304H, 312, 321H, 347, 347H, UNS S30409, S32109, S34709, S30400, S32100, S34700							
APPROVALS	CE							
WELDING POSITIONS								
TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)	C	Si	Mn	P	S	Cr	Ni	Mo
	0.02	0.55	2	0.02	0.01	21	10	0.5
ALL WELD MECHANICAL PROPERTIES	Heat Treatment	R _{P0,2} MPa	R _m MPa	A5 (%)				
	As Welded /	450	600					
REDRYING TEMPERATURE	Not required							
GAS ACCORDING EN 14175								