


CEWELD MA 6500 Tig

TYPE	Solid welding wire for Hardfacing						
APPLICATIONS	MA 6500 Tig is for Hardfacing and or clad layers against high impact combined with abrasion for use with pure Argon						
PROPERTIES	He offers almost full hardness in the first layer and can be applied without any risk of cracking. Multiple layers or sandwich layers are possible before Hardfacing and will help to increase the hardness (wear resistance) from the hard-faced layer.						
CLASSIFICATION	EN ISO	14700: S Fe3					
	DIN	8555: TIG 6-GZ-50-T					
	F-nr	71					
	W.Nr.	1.2344					
SUITABLE FOR	MA 6500 Tig is a solid welding rod for rebuilding parts with a hardness up to 55 HRc.						
APPROVALS	No Approvals Found						
WELDING POSITIONS							
TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)	C	Mn	Cr	Ni	Mo	V	Fe
	0.4	0.5	5	0.1	1.3	1	Rem.
ALL WELD MECHANICAL PROPERTIES	Heat Treatment	R _{p0,2} MPa	R _m MPa	A5 (%)	Hardness Rockwell C		
	As Welded /				Avg. 55		
REDRYING TEMPERATURE	Not required						
GAS ACCORDING EN 14175	I1						