





TYPE Solid Mag stainless steel welding wire with high Molybdenium content.

APPLICATIONS For welding stabilized and un-stabilized CrNiMo(N) type of steels with high corrosion resistance.

> Also suitable for dissimilar welds between steel and stainless steel or dissimilar stainless steels. CEWELD 317L has good resistance to general corrosion and pitting due to its high content of molybdenum. The alloy has a low carbon content which makes it particularly recommended when there is a risk of intergranular corrosion. The alloy is used in severe corrosion conditions such as in

the petrochemical, pulp, cotton and paper industries.

PROPERTIES Austenitic, non magnetic stainless steel alloy with high mechanical properties and excellent

weldability, corrosion resistance is better than AISI 316 due to the high Mo. content. Suitable for use

up to 400°C

CLASSIFICATION **AWS** A 5.9: ER317L

> EN ISO 14343-A: G 18 15 3 L

F-nr 6 FΜ 5 W.Nr. 1.4438

SUITABLE FOR 1.4429, 1.4434, 1.4435, 1.4436, 1.4438, 1.4439, 1.4453, 1.4583,

X2CrNiMoN 17 13 5, X2CrNiMoN 17 13 3, X2CrNiMo 18 15 4, X10CrNiMoNb 18 12, X2CrNiMoN17-13-

3, X2CrNiMoN18-12-4, X2CrNiMo18-14-3, X3CrNiMnMoN19-16

UNS S31600, S31653, S31703, S31726, S31753 AISI 316Cb, 316L, 316LN, 317L, 317LN, 317LMN

APPROVALS CE

WELDING POSITIONS



TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)

ALL WELD MECHANICAL

PROPERTIES

								Cu
0.01	0.45	1.4	0.02	0.01	18.8	13.6	3.5	0.12

 $R_{P0,2}$ Heat Rm A5 Impact Energy (J) ISO-V MPa MPa (%)RT -40°C Treatment As Welded / 400 590 35 87 70

REDRYING TEMPERATURE Not required

GAS ACCORDING EN 14175 M13, M12





CEWELD 317L

317L 0,8MM	Type	KG/unit	EANCode	
	BS-300	15	8720663415257	
317L 1,0MM	Type	KG/unit	EANCode	
	BS-300	15	8720682051221	
317L 1,2MM	Type	KG/unit	EANCode	
	BS-300	15	8720663415264	
317L 1,6MM	Type	KG/unit	EANCode	
	BS-300	15	8720663415271	