










CEWELD Al 99,5 Ti Tig

TYPE	Pure aluminum filler metal for Tig welding						
APPLICATIONS	Aluminium wire for welding mostly pure aluminium (maximum 0,5% of alloyed elements). Applications in chemistry, electronics, construction and food industries.						
PROPERTIES	This pure aluminum filler metal offers excellent weldability when properly cleaned prior to welding. Heavy parts and thicker plates should be preheated (150°C), prior to welding						
CLASSIFICATION	AWS	A 5.10: ER1450					
	EN ISO	18273: S Al 1450 (Al99,5Ti)					
	F-nr	21					
SUITABLE FOR	Cast aluminium special repairs, Al99,0 Al.99,5 Al.99,7 E-Al						
APPROVALS	CE						
WELDING POSITIONS	      						
TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)	Si	Mn	Ti	Fe	Cu	Zn	Al
	0.2	0.02	0.15	0.2	0.02	0.03	99.6
ALL WELD MECHANICAL PROPERTIES	Heat Treatment	R _{P0,2} MPa	R _m MPa	A5 (%)			
	As Welded /1h	30	80	40			
REDRYING TEMPERATURE	Not required						
GAS ACCORDING EN 14175	I1, I3						