



CEWELD AA 310

TYPE	Rutile flux cored stainless steel welding wire for M21 and Co2 gas. (Type 25 20)															
APPLICATIONS	Common applications include industrial furnaces, annealing chambers, fused salt treatment installations and boiler parts, as well as heat exchangers															
PROPERTIES	For welding heat-resistant austenitic steels of the 25% Cr, 20% Ni types. AA 310 has good general oxidation resistance, especially at high temperatures, due to its high Cr content. The alloy is fully austenitic and is therefore sensitive to hot cracking. The temperature limits for use under intermittent oxidation depend on cycle frequency. In no case shall a temperature of 1000°C be exceeded. This alloy can withstand relatively severe thermic shock, and is superior to type 309L.															
CLASSIFICATION	<table border="0"> <tr> <td>AWS</td> <td>A 5.22: E310T0-1</td> </tr> <tr> <td>AWS</td> <td>A 5.22: E310T0-4</td> </tr> <tr> <td>EN ISO</td> <td>17633-A: T 25 20 R C1 3</td> </tr> <tr> <td>EN ISO</td> <td>17633-A: T 25 20 R M21 3</td> </tr> <tr> <td>F-nr</td> <td>6</td> </tr> <tr> <td>FM</td> <td>5</td> </tr> <tr> <td>W.Nr.</td> <td>1.4842</td> </tr> </table>	AWS	A 5.22: E310T0-1	AWS	A 5.22: E310T0-4	EN ISO	17633-A: T 25 20 R C1 3	EN ISO	17633-A: T 25 20 R M21 3	F-nr	6	FM	5	W.Nr.	1.4842	
AWS	A 5.22: E310T0-1															
AWS	A 5.22: E310T0-4															
EN ISO	17633-A: T 25 20 R C1 3															
EN ISO	17633-A: T 25 20 R M21 3															
F-nr	6															
FM	5															
W.Nr.	1.4842															
SUITABLE FOR	<p>ISO 15608: 8.1 Austenitic ≤ 19 % Cr , TÜV 1000: Gr. 21-30, Type: 25% Cr, 22%Ni 1.4710, 1.4713, 1.4724, 1.4726, 1.4742, 1.4745, 1.4762, 1.4823, 1.4826, 1.4828, 1.4832, 1.4835, 1.4837, 1.4840, 1.4841, 1.4845, 1.4846, 1.4848, 1.4849, 253MA, X15CrNiSi 25 20, G-X40CrNiSi 25 12, G-X15CrNi 25 20, X8CrNi25-21, GX40CrNiSi22-10, X15CrNiSi20-12, 310, 310S, CK20, 305, 314, 725LN, 316L ASTM A297 HF / A297HJ UNS: S31000, S31008, S31050, S31603</p>															
APPROVALS	CE															
WELDING POSITIONS																
TYPICAL CHEMICAL ANALYSIS OF WELD METAL (%)	<table border="1"> <thead> <tr> <th>C</th> <th>Si</th> <th>Mn</th> <th>P</th> <th>Cr</th> <th>Ni</th> <th>S</th> </tr> </thead> <tbody> <tr> <td>0.18</td> <td>0.6</td> <td>2.1</td> <td>0.015</td> <td>25.5</td> <td>21</td> <td>0.015</td> </tr> </tbody> </table>	C	Si	Mn	P	Cr	Ni	S	0.18	0.6	2.1	0.015	25.5	21	0.015	
C	Si	Mn	P	Cr	Ni	S										
0.18	0.6	2.1	0.015	25.5	21	0.015										
ALL WELD MECHANICAL PROPERTIES	<table border="1"> <thead> <tr> <th>Heat Treatment</th> <th>R_{P0,2} MPa</th> <th>R_m MPa</th> <th>A₅ (%)</th> <th>Impact Energy (J) ISO-V</th> </tr> </thead> <tbody> <tr> <td>As Welded /</td> <td>410</td> <td>600</td> <td>35</td> <td>RT</td> </tr> <tr> <td></td> <td></td> <td></td> <td></td> <td>75</td> </tr> </tbody> </table>	Heat Treatment	R _{P0,2} MPa	R _m MPa	A ₅ (%)	Impact Energy (J) ISO-V	As Welded /	410	600	35	RT					75
Heat Treatment	R _{P0,2} MPa	R _m MPa	A ₅ (%)	Impact Energy (J) ISO-V												
As Welded /	410	600	35	RT												
				75												
REDRYING TEMPERATURE	140°C / 24 hr															
GAS ACCORDING EN 14175	M21, C1															



CEWELD AA 310

AA 310 1,2MM

Type	KG/unit	EANCode
BS-300	15	8720663416094