



CEWELD AA 309 LMoP

TYPE	Stainless steel Rutile flux cored weldig wire. (Typ 309LMo, 23 12 2 L, 1.4459)																						
APPLICATIONS	CEWELD® AA 309 LMoP you can use for cladding applications in case a AISI 316 is required in the first layer, suitable for dissimilar welding of steel to stainless steel, heat resistant up to 1050 degrees Celsius																						
PROPERTIES	CEWELD® AA 309 LMoP is a flux cored wire with rapidly solidifying slag (P in Standard) support for high productivity welding in all positions. Excellent for use on ceramic backing strips. The slag is self detaching and offers extra protection to obtain X-ray proof weld seams with practically no spatters. Better wetting and welding properties with more productivity compared to solid wires.																						
CLASSIFICATION	<table border="0"> <tr> <td>AWS</td> <td>A 5.22: E309LMoT1-4</td> </tr> <tr> <td>AWS</td> <td>A 5.22: E309LMoT1-1</td> </tr> <tr> <td>EN ISO</td> <td>17633-A: T 23 12 2 L P M21 1</td> </tr> <tr> <td>EN ISO</td> <td>17633-A: T 23 12 2 L P C1 1</td> </tr> <tr> <td>F-nr</td> <td>6</td> </tr> <tr> <td>FM</td> <td>5</td> </tr> <tr> <td>W.Nr.</td> <td>1.4459</td> </tr> </table>	AWS	A 5.22: E309LMoT1-4	AWS	A 5.22: E309LMoT1-1	EN ISO	17633-A: T 23 12 2 L P M21 1	EN ISO	17633-A: T 23 12 2 L P C1 1	F-nr	6	FM	5	W.Nr.	1.4459								
AWS	A 5.22: E309LMoT1-4																						
AWS	A 5.22: E309LMoT1-1																						
EN ISO	17633-A: T 23 12 2 L P M21 1																						
EN ISO	17633-A: T 23 12 2 L P C1 1																						
F-nr	6																						
FM	5																						
W.Nr.	1.4459																						
SUITABLE FOR	<p>ISO 15608: 8.1 Austenitic ≤ 19 % Cr , TÜV 1000: Gr. 21-30, 1.4583, 1.4435, 1.4436, 1.4404, 1.4406, 1.4408, 1.4401, 1.4571, 1.4580, 1.4406, 1.4521, 1.4301, 1.4306, X102CrNiMoNb 18 12, X2CrNiMo 18 14 3 (TP), X4CrNiMo 17 13 3, X2CrNiMo 17 12 2 (TP), X 5CrNiMo 19 11 2, X4CrNiMo 17 12 2 (TP), X6CrNiMo 17 12 2, X6CrNiMoNb 17 12 3, X2CrNiMoN 17 12 3 (TP), X2CrMoTi18-2 316Cb, 316L, 316LN, 316H, 316, 316Ti, 316Cb, 316LN, 444 S31640, S31603, S31653, S31600, S31630, S44400</p>																						
APPROVALS	CE																						
WELDING POSITIONS																							
TYPICAL CHEMICAL ANALYSIS OF WELD METAL (%)	<table border="1"> <thead> <tr> <th>C</th> <th>Si</th> <th>Mn</th> <th>P</th> <th>Cr</th> <th>Ni</th> <th>Mo</th> <th>S</th> <th>FN</th> <th>FS</th> <th>FNW</th> </tr> </thead> <tbody> <tr> <td>0.025</td> <td>0.55</td> <td>0.9</td> <td>0.015</td> <td>23</td> <td>12.5</td> <td>2.5</td> <td>0.015</td> <td>18</td> <td>17</td> <td>25</td> </tr> </tbody> </table>	C	Si	Mn	P	Cr	Ni	Mo	S	FN	FS	FNW	0.025	0.55	0.9	0.015	23	12.5	2.5	0.015	18	17	25
C	Si	Mn	P	Cr	Ni	Mo	S	FN	FS	FNW													
0.025	0.55	0.9	0.015	23	12.5	2.5	0.015	18	17	25													
ALL WELD MECHANICAL PROPERTIES	<table border="1"> <thead> <tr> <th rowspan="2">Heat Treatment</th> <th rowspan="2">R_{P0,2} MPa</th> <th rowspan="2">R_m MPa</th> <th rowspan="2">A₅ (%)</th> <th colspan="2">Impact Energy (J) ISO-V</th> </tr> <tr> <th>RT</th> <th>-40°C</th> </tr> </thead> <tbody> <tr> <td>As Welded /</td> <td>400</td> <td>600</td> <td>32</td> <td>110</td> <td>27</td> </tr> </tbody> </table>	Heat Treatment	R _{P0,2} MPa	R _m MPa	A ₅ (%)	Impact Energy (J) ISO-V		RT	-40°C	As Welded /	400	600	32	110	27								
Heat Treatment	R _{P0,2} MPa					R _m MPa	A ₅ (%)	Impact Energy (J) ISO-V															
		RT	-40°C																				
As Welded /	400	600	32	110	27																		
REDRYING TEMPERATURE	140°C / 24 hr																						
GAS ACCORDING EN 14175	M21, C1																						



CEWELD AA 309 LMoP

AA 309 LMoP 1,2MM

Type	KG/unit	EANCode
BS-300	15	8720663413796
D-200	5	8720663413802