


# CEWELD G1

TYPE	Copper-coated unalloyed solid rod for gas welding. (OI, R45)					
APPLICATIONS	The CEWELD G1 is designed for gas welding unalloyed steels. This process is primarily used for welding plates, pipes, and other profiles where low strength is required.					
PROPERTIES	The CEWELD G1 is designed for gas welding unalloyed steels with a minimum tensile strength of 250 MPa. The resulting joints are homogeneous and soft, and the mechanical properties are excellent.					
CLASSIFICATION	AWS	A 5.2: R45				
	EN ISO	20378: O I				
	F-nr	6				
	FM	1				
	W.Nr.	1.0324				
SUITABLE FOR	<b>Re ≤ 235 MPa (55 ksi) ISO 15608: 1.1( ReH &lt; 235 MPa )</b> 1.0034, 1.0035, 1.0037, 1.0038, 1.0039, 1.0044, 1.0108, 1.0111, 1.0114, 1.0115, 1.0116, 1.0118, 1.0119, 1.0120, 1.0122, 1.0128, 1.0166, 1.0167, 1.0170, 1.0171, 1.0252, 1.0252, 1.0253, 1.0254, 1.0255, 1.0308 E 190, S185, S235JRG2, S235JR S235JRH, P235S, S235J2G3, P235TR1, P235TR2, P235GH, P235GH, P235GH, P195GH, P245GH, L245ME, GE200, C 22.3, C 21 , GE240, P215NL, P275N, S275N, S275NL, GP240GH, P275SL, <b>ASTM:</b> A36, A106 grades A/B, A139 grade A, A216 grades WCA/WCB/WCC, A234 grade WPB					
APPROVALS	CE					
WELDING POSITIONS						
TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)	C 0.08		Si 0.1		Mn 0.5	
ALL WELD MECHANICAL PROPERTIES	Heat Treatment As Welded /	R <sub>P0,2</sub> MPa 300	R <sub>m</sub> MPa 400	A5 (%) 20	Impact Energy (J) ISO-V RT 35	0°C 30
REDRYING TEMPERATURE	Not required					
GAS ACCORDING EN 14175	None					