



# CEWELD L-Ag34Sn

TYPE	High silver containing cadmium free brazing alloy.			
APPLICATIONS	L-Ag30Sn is for brazing a weight range of different metals in maintenance and repair with excellent strength, Boiler making, tubing, cooling equipment etc.			
PROPERTIES	The presence of tin improves the fluidity and is useful to increase the activity of the flux. Do not use this alloy above working temperatures of 200 °C. Flux/Paste: CEWELD Super-Flux			
CLASSIFICATION	EN ISO	17672: Ag 134		
SUITABLE FOR	Brazing: Steels, Copper, Copper alloys, Stainless steel, Nickel and Nickel alloys. Also suitable for dissimilar joints between these metals.			
APPROVALS	No Approvals Found			
WELDING POSITIONS				
TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)	Cu 36	Zn 28	Sn 2.5	Ag 34
ALL WELD MECHANICAL PROPERTIES	Heat Treatment As Welded /	R <sub>P0,2</sub> MPa 450	A5 (%)	
REDRYING TEMPERATURE	Not required			
GAS ACCORDING EN 14175				



# CEWELD L-Ag34Sn

L-AG34SN 1,0 X 500MM

Type	KG/unit	EANCode
	1	8720663421999

L-AG34SN 1,5 X 500MM

Type	KG/unit	EANCode
	1	8720663422019

L-AG34SN 2,0 X 500MM

Type	KG/unit	EANCode
	1	8720663422002