

CEWELD L-Ag5P

TYPE Copper Phosphorus Silver Brazing Alloy.

APPLICATIONS Particularly recommended for sanitary and refrigerating equipment. Suitable for working temperatures up to 200 °C

PROPERTIES Excellent flowing alloy with high purity offering strong brazing joints. Do not use in a sulphurous environment. Flux/Paste: CEWELD Super-Flux

CLASSIFICATION AWS A 5.8: BCuP-3
 EN ISO 17672: CuP 281
 F-nr 103

SUITABLE FOR Copper to Copper (without flux). Brass, Copper and Copper-Tin Alloys (with flux).

APPROVALS No Approvals Found

WELDING POSITIONS



TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)


Cu	Ag	P
Rem.	5	6

ALL WELD MECHANICAL PROPERTIES

Heat Treatment	R _{p0,2} MPa	R _m MPa	A ₅ (%)
As Welded /		250	

REDRYING TEMPERATURE Not required

GAS ACCORDING EN 14175



CEWELD L-Ag5P

L-AG5P 1,5MM

Type	KG/unit	EANCode
D-300	10,11	8720663421487