



CEWELD Alu-Flux

TYPE	Flux for aluminium brazing
APPLICATIONS	Alu-Fux is for brazing from Aluminium and Aluminium Alloys with a working range from 350 to 550 °C
PROPERTIES	Usually combined with AlSi12 or AlSi5 filler metal.
CLASSIFICATION	EN ISO 18496: FL20
SUITABLE FOR	Brazing for Aluminium and Aluminium Alloys with a working range from 350 to 550 °C. Usually combined with AlSi12 or AlSi5 filler metal.
APPROVALS	No Approvals Found
WELDING POSITIONS	
REDRYING TEMPERATURE	Not required
GAS ACCORDING EN 14175	



CEWELD Alu-Flux

ALU-FLUX NMM

Type	KG/unit	EANCode
Jar	0,25	8720663423016