



CEWELD NiCu30Mn Tig

TYPE GTAW welding wire for Monel 400 and similar alloys.

APPLICATIONS Shipbuilding, seawater evaporation plants, tubes, pump building, offshore etc.

PROPERTIES CEWELD® NiCu30Mn is a Nickel - Copper weld metal and has properties similar to "Monel 400". It has good strength and resists corrosion in many media, including sea water, salts and reducing acids. The weld metal is not age hardenable and when used to join Monel K-500 it has lower strength than the base metal.

CLASSIFICATION

AWS	A 5.14: ERNiCu-7
EN ISO	18274: S Ni 4060(NiCu30Mn3Ti)
F-nr	42
FM	6
W.Nr.	2.4377
W.Nr.	~2.4366

SUITABLE FOR

E Ni 4060 (NiCu30Mn3Ti)
 2.4360, 2.4361, 2.4365, 2.4375, (2.0872, 2.0882, 2.0890)
 NiCu30Fe, NiCu30Al, G-NiCu 30 Nb, LC-NiCu 30 Fe,
ASTM B127, B163, B164, B165
UNS N04400
 Monel 400, Monel R405, Monel K-500
 Alloy K500 and dissimilar welding between these Alloys.

APPROVALS No Approvals Found

WELDING POSITIONS

TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)

C	Si	Mn	Ni	Ti	Fe	Cu	Al
0.1	1	3	65	2.5	2	30	0.9

ALL WELD MECHANICAL PROPERTIES

Heat Treatment	R _{P0,2} MPa	R _m MPa	A ₅ (%)	Impact Energy (J) ISO-V RT
As Welded /	315	500	32	100

REDRYING TEMPERATURE Not required

GAS ACCORDING EN 14175 I1



CEWELD NiCu30Mn Tig

NICU30MN TIG 1,6 X 1000MM	Type	KG/unit	EANCode
	Tube	5	8720663418036
NICU30MN TIG 1,6 X 914MM	Type	KG/unit	EANCode
	Tube	4,54	8720663418029
NICU30MN TIG 2,0 X 1000MM	Type	KG/unit	EANCode
	Tube	5	8720663418043
NICU30MN TIG 2,0 X 914MM	Type	KG/unit	EANCode
	Tube	4,54	8720663417664
NICU30MN TIG 2,4 X 1000MM	Type	KG/unit	EANCode
	Tube	5	8720663418050
NICU30MN TIG 2,4 X 914MM	Type	KG/unit	EANCode
	Tube	4,54	8720663418067
NICU30MN TIG 3,2 X 1000MM	Type	KG/unit	EANCode
	Tube	5	8720663418074
NICU30MN TIG 3,2 X 914MM	Type	KG/unit	EANCode
	Tube	4,54	8720663418081