










CEWELD NiCrMo 686 CPT

TYPE	Nickel-Chromium-Molybdenum based alloy for gas metal arc welding												
APPLICATIONS	NiCrMo 686 is of great value for service environments requiring general corrosion-resistance in HCl or sulfuric acid; for resistance to crevice corrosion in hot, concentrated acid chloride solutions such as sulfur dioxide saturated NaCl solutions and oxidizing chloride solutions; and for resistance to intergranular attack, and for resistance to intergranular attack, after sensitization, in highly oxidizing environments.												
PROPERTIES	NiCrMo 686 (UNS N06686/W.Nr. 2.4606) is a single-phase, austenitic Ni-Cr-Mo-W alloy offering outstanding corrosion-resistance in a range of severe environments. Its high nickel (Ni) and molybdenum (Mo) provide good resistance in reducing conditions, and high chromium (Cr) offers resistance to oxidizing media. Molybdenum (Mo) and tungsten (W) aid resistance to localized corrosion such as pitting. Iron (Fe) is closely controlled to enhance properties. Low carbon (C) helps minimize grain boundary precipitation to maintain corrosion-resistance in the heat-affected zones of welded joints. Resistance to general, pitting and crevice corrosion increases with the alloying (Cr+Mo+W) content, and NiCrMo 686 scores higher than competitive materials.												
CLASSIFICATION	AWS	A 5.14: ERNiCrMo-14											
	EN ISO	18274: S Ni 6686 (NiCr21Mo16W4)											
	F-nr	43											
	FM	6											
	W.Nr.	~2.4606											
SUITABLE FOR	Duplex, super-duplex and super-austenitic stainless steels, nickel alloys such as UNS N06059 and N06022, INCONEL alloy C-276, and INCONEL alloys 622, C22, 625, and 686 CPT, Alloy 31, 1.4562, alloy 59, alloy C4, C2000, W86026												
APPROVALS	No Approvals Found												
WELDING POSITIONS	<div></div>												
TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)	C	Si	Mn	P	S	Cr	Ni	Mo	Ti	Fe	W	Cu	Al
	0.03	0.06	0.3	0.002	0.001	21	58	16	0.1	0.8	3.5	0.01	0.23
ALL WELD MECHANICAL PROPERTIES	Heat Treatment		R _{P0,2} MPa	R _m MPa	A5 (%)								
	As Welded /			760									
REDRYING TEMPERATURE	Not required												
GAS ACCORDING EN 14175	I1, I3												



CEWELD NiCrMo 686 CPT

NICRMO 686 CPT 0,8MM

Type	KG/unit	EANCode
BS-300	15	8720663419484

NICRMO 686 CPT 1,0MM

Type	KG/unit	EANCode
BS-300	15	8720663419507

NICRMO 686 CPT 1,14MM

Type	KG/unit	EANCode
BS-300	13,6	8720663419521

NICRMO 686 CPT 1,6MM

Type	KG/unit	EANCode
BS-300	15	8720663419538