



CEWELD ERTi-12 Tig

TYPE	Titanium Tig welding wire grade 12						
APPLICATIONS	This alloy finds his applications in chemical industry and offers excellent Weldability. Often recommended for pressure vessels and piping for its superior strength alone.						
PROPERTIES	ERTi-12. Grade 12 (Ti 0.8Ni0.3Mo) is an intermediate strength grade originally developed to provide enhanced crevice-corrosion resistance in high temperature brines, but at lower cost than Grade 7. The improved performance is believed to be the result of Ni++ and Mo++ ions that alter the surface electrochemistry of the material in the crevice or under a surface deposit. Grade 12 has better elevated temperature properties than Grade 2 or 3 and is sometimes specified for pressure vessels or piping for its superior strength alone.						
CLASSIFICATION	AWS EN ISO F-nr	A 5.16: ERTi-12 24034: S Ti 3401 / TiNi0,7Mo0,3 51					
SUITABLE FOR	Titanium grade 12, Grade 7, Grade 2 and Grade 3						
APPROVALS	No Approvals Found						
WELDING POSITIONS							
TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)	C 0.02	H 0.005	N 0.01	O 0.12	Fe 0.1	Ni 0.8	Ti Rem.
ALL WELD MECHANICAL PROPERTIES	Heat Treatment As Welded /	R _{P0,2} MPa 345	R _m MPa 480	A5 (%) 20			
REDRYING TEMPERATURE	Not required						
GAS ACCORDING EN 14175	I1						



CEWELD ERTi-12 Tig

ERTI-12 TIG 1,6 X 1000MM	Type	KG/unit	EANCode
	Tube	2,5	8720663406477
ERTI-12 TIG 2,0 X 1000MM	Type	KG/unit	EANCode
	Tube	2,5	8720663406484
ERTI-12 TIG 2,4 X 1000MM	Type	KG/unit	EANCode
	Tube	2,5	8720663406491
ERTI-12 TIG 3.2 X 1000MM	Type	KG/unit	EANCode
	Tube	2,5	8720663406507