





Ni+Co

1.8

TYPE Copper aluminium nickel alloy for Mig welding and brazing

APPLICATIONS Low alloyed aluminum bronze, particularly suitable for joint welds on ferritic and austenitic steels.

Good flowing properties with good cover groove, also suitable for joint welds on steels and copper. For multiplayer welding on steels, pulsed arc welding is recommended. Amazing results are obtained on stainless steel sheet metal due to less heat input, higher travel speed and less cleaning hours. Containers, valve control chambers, exhaust parts, thin sheet welding (steel and specially

stainless steel) Ship propellers, shipbuilding, pump building, shafts, guide grooves etc.

PROPERTIES Sound, pore free deposits on ferrous and non-ferrous base materials with excellent wetting. Due to

the excellent wetting and low melting point welding speeds can be achieved upto 2 mtr/min. The

weld deposit offers a corrosion resistance similar to AISI 304.

CLASSIFICATION EN ISO 24373: Cu 6161 / CuAl5Ni2Mn

F-nr 36

SUITABLE FOR W.Nrs: 2.0916,2.0920, 2.0928, 2.0932, 2.0936, 2.0940, 2.0960, 2.0962, 2.0966, 2.0970, 2.0978,

2.0980.

APPROVALS No Approvals Found

WELDING POSITIONS



0.5

TYPICAL CHEMICAL ANALYSIS OF WELD METAL

(%)

ALL WELD MECHANICAL PROPERTIES

Heat	R _{P0,2}	Rm	A5	Impact Energy (J) ISO-V
Treatment	MPa	MPa	(%)	RT
As Welded /1h		353	45	161

REDRYING TEMPERATURE Not required

GAS ACCORDING EN 14175 11







CUAL5NI2 1,0MM

Type	KG/unit	EANCode
BS-300	15	8720663409140