



CEWELD CuSn

TYPE	Copper welding wire alloyed with Sn for Mig and Tig welding				
APPLICATIONS	Boilers and tubes out of copper or copper alloys, oven soldering etc..				
PROPERTIES	<ul style="list-style-type: none"> • High quality alloyed copper wire • Sound, pore free deposits and good electrical conductivity • Excellent corrosion resistance 				
CLASSIFICATION	AWS	A 5.7: ERCu			
	EN ISO	24373: Cu 1898 / CuSn1			
	F-nr	31			
	W.Nr.	~2.1006			
SUITABLE FOR	Bronze alloy with minimally 0.8 tin for virtually all welding procedures. Very good deoxidisation. Surfacing and joining of Cu and copper- alloys. Widely used in oven soldering. 2.0040 - OF-Cu, 2.0070 - SE-Cu, 2.0076 - SW-Cu, 2.0090 - SF-Cu				
APPROVALS	No Approvals Found				
WELDING POSITIONS					
TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)	Si	Mn	Cu	Sn	
	0.3	0.3	98.5	0.8	
ALL WELD MECHANICAL PROPERTIES	Heat Treatment	R _{p0,2} MPa	R _m MPa	A5 (%)	Hardness Brinell Hardness
	As Welded /		220		Avg. 60
REDRYING TEMPERATURE	Not required				
GAS ACCORDING EN 14175	I1, I3				



CEWELD CuSn

CUSN 0,8MM

Type	KG/unit	EANCode
D-300	15	8720663408624

CUSN 1,0MM

Type	KG/unit	EANCode
BS-300	15	8720663408631

CUSN 1,2MM

Type	KG/unit	EANCode
BS-300	15	8720663408648
Drum	250	8720682051528

CUSN 1,6MM

Type	KG/unit	EANCode
BS-300	15	8720663408655