




CEWELD FL 160

TYPE	High basic SAW flux with low hydrogen content.								
APPLICATIONS	Boiler works, vessel and structural steel works, tanks and pressure vessels, offshore lifting applications, platforms etc..								
PROPERTIES	FL 160 is a highly basic SAW flux with low hydrogen content. Basicity: about 3 (according to Boniszewski) Current: DC or AC, in single or multi-wires Grain size: 2-20								
CLASSIFICATION	EN ISO 14174: SA FB 1 55 AC H5								
SUITABLE FOR	S355, S420, S460, X65, X70, X80								
APPROVALS	No Approvals Found								
WELDING POSITIONS									
TYPICAL CHEMICAL COMPOSITION IN WEIGHT (%)	<table border="1"><thead><tr><th>Al₂O₃</th><th>CaF₂</th><th>SiO₂</th><th>CaO+MgO</th></tr></thead><tbody><tr><td>20</td><td>20</td><td>15</td><td>40</td></tr></tbody></table>	Al ₂ O ₃	CaF ₂	SiO ₂	CaO+MgO	20	20	15	40
Al ₂ O ₃	CaF ₂	SiO ₂	CaO+MgO						
20	20	15	40						
REDRYING TEMPERATURE	Not required								
GAS ACCORDING EN 14175									



CEWELD FL 160

FL 160 0,2 - 2,0MM

Type	KG/unit	EANCode
Bag	25	8720663404008
Bag	25	8720663404015